

NBS MONOGRAPH 29

Thermal Expansion of Technical Solids at Low Temperatures

A Compilation From the Literature



**U.S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS**

THE NATIONAL BUREAU OF STANDARDS

Functions and Activities

The functions of the National Bureau of Standards are set forth in the Act of Congress, March 3, 1901, as amended by Congress in Public Law 619, 1950. These include the development and maintenance of the national standards of measurement and the provision of means and methods for making measurements consistent with these standards; the determination of physical constants and properties of materials; the development of methods and instruments for testing materials, devices, and structures; advisory services to government agencies on scientific and technical problems; invention and development of devices to serve special needs of the Government; and the development of standard practices, codes, and specifications. The work includes basic and applied research, development, engineering, instrumentation, testing, evaluation, calibration services, and various consultation and information services. Research projects are also performed for other government agencies when the work relates to and supplements the basic program of the Bureau or when the Bureau's unique competence is required. The scope of activities is suggested by the listing of divisions and sections on the inside of the back cover.

Publications

The results of the Bureau's work take the form of either actual equipment and devices or published papers. These papers appear either in the Bureau's own series of publications or in the journals of professional and scientific societies. The Bureau itself publishes three periodicals available from the Government Printing Office: The Journal of Research, published in four separate sections, presents complete scientific and technical papers; the Technical News Bulletin presents summary and preliminary reports on work in progress; and Basic Radio Propagation Predictions provides data for determining the best frequencies to use for radio communications throughout the world. There are also five series of nonperiodical publications: Monographs, Applied Mathematics Series, Handbooks, Miscellaneous Publications, and Technical Notes.

Information on the Bureau's publications can be found in NBS Circular 460, Publications of the National Bureau of Standards (\$1.25) and its Supplement (\$1.50), available from the Superintendent of Documents, Government Printing Office, Washington 25, D.C.

UNITED STATES DEPARTMENT OF COMMERCE • Luther H. Hodges, *Secretary*

NATIONAL BUREAU OF STANDARDS • A. V. Astin, *Director*

Thermal Expansion of Technical Solids at Low Temperatures

A Compilation From the Literature

Robert J. Corruccini and John J. Gniewek



National Bureau of Standards Monograph 29

Issued May 19, 1961

For sale by the Superintendent of Documents, U.S. Government Printing Office
Washington 25, D.C. - Price 20_cents

Thermal Expansion of Technical Solids at Low Temperatures *

A Compilation From the Literature

Robert J. Corruccini and John J. Gniewek

Tables are given of the linear contraction relative to 293 °K, $(L_{293} - L_T)/L_{293}$, and the linear expansion coefficient, $dL/L_{293}dT$, of thirty elements, forty-five alloys, twenty-two other inorganic substances and twenty plastics and elastomers in the temperature range, 0 to 300 °K.

Introduction

This publication was intended to fill a need among designers of cryogenic equipment for a compilation of thermal expansion data on cryogenic materials. The literature search relied primarily on Physics Abstracts and is believed to provide complete coverage of the published literature through 1958. It was found that very few additional references were derived from subsequently searching other sources.

Wherever possible, data have been presented throughout the range, 0 to 300 °K. However, the region below 100° K is of predominant importance in cryogenic engineering, and, hence, many substances of interest have been omitted because data were not available below 100 °K.

Certain substances which are usually used as fluids in cryogenics have been omitted. These are helium, hydrogen, deuterium, neon, nitrogen, carbon monoxide, fluorine, argon, oxygen, air, and methane. Various properties of all phases of these substances are being compiled separately at this laboratory.

The published data usually consisted of unsmoothed values of length change. It was necessary to adjust these to our adopted reference temperature of 293 °K, to smooth and interpolate at rounded values of temperature, and to differentiate. Most of the results are given in table 2.

The references on which the resulting data were based are indicated in each table as "Sources of above data". All other sources of low temperature data for each substance are listed as "Other references". The selection of best sources will not be justified in detail. In general it was based on the precision of the data, the original authors' estimates of accuracy, and the quality of the samples. The bibliography gives complete references to the sources associated with the tables of data. In addition, it contains selected references on theory, experimental techniques, and measurements of other substances which were outside our scope but which were thought to be of more than average interest. The bibliography attempts to be complete only with regard to the substances listed in table 1.

*This work was partly supported by Wright Air Development Center, Air Research and Development Command U.S. Air Force.

Table 3 gives data on some miscellaneous substances that did not fit into the format of table 2. It was not practical to extend these data in any way, and so they are quoted almost verbatim from the original sources.

Materials of construction often are anisotropic as a result of forming operations. This is especially noticeable with metals having highly anisotropic crystal lattices, such as zinc, and with plastics based on chain polymers. The degree of preferred orientation in such materials may be uncontrolled and, consequently, measurements of the linear thermal expansion may vary greatly with sample history and orientation. Measurements that are made in only one direction of such a material can be given little weight. Wherever a complete set of linear expansions along mutually perpendicular directions were available, we calculated the mean linear expansion for presentation in table 2. This quantity is to a very good approximation one-third the volume expansion and is the linear expansion that would be observed in the absence of preferred orientation. Although such a condition may not often be perfectly realizable, it represents average behavior and is a precisely defined physical quantity. In order to show the maximum possible variation in the linear expansion with orientation we have given in table 4 representative values along the principal crystallographic axes for some of the more anisotropic elements. These data were taken directly from the literature without smoothing.

Thermal cycling of polycrystalline materials in which the crystallites are anisotropic produces internal stresses. In extreme cases plastic deformation can result. This has been observed in tin, cadmium, and zinc by Boas and Honeycombe [1947] and in graphite by Hidnert [1934] and Baskin and Meyer [1955].

There are two main classes of experimental methods using macroscopic and X-ray lattice parameter techniques, respectively. In a few cases [Glover, 1954; Gott, 1942; Smith, 1954] appreciable differences in thermal expansion by the two methods have been found, amounting to over 10 percent at the worst. However, others have found no difference exceeding experimental error except near the melting point [Austin, Saini, Weigle, and Pierce, 1940; Berry, 1953; Connell and Martin, 1951; van Duijn and van Galen, 1957; Feder and Nowick, 1958; Hume-Rothery and Andrews, 1942; Hume-Rothery and Boulton, 1949; Hume-Rothery and Strawbridge, 1947; Simmons and Baluffi,

1959, 1960; Wagner and Beyer, 1936]. Such differences, if real, would require high concentrations of vacancies or nonuniform distribution of lattice defects. The dimensional effects produced by lattice defects have been analyzed by Eshelby [1953, 1954, 1956], Miller and Russell [1952, 1953], and Toupin and Rivlin [1960]. The effect of impurities in metals is illustrated by measurements due to Hume-Rothery and Boulbee [1949]. The effect of elastic strain has been examined by Rosenfield and Averbach [1956] and the effect of plastic deformation has been examined by Hordon, Lement, and Averbach [1958].

Smoothing and interpolation were necessary with many substances in order to obtain tables that were sufficiently detailed to be useful. It was a common situation to find published values of length change at fairly small intervals from ambient temperature to about liquid air temperature, then a single value (often from a different source) of the length change between 78, 83, or 90 °K and 20 °K. By adjusting these length changes to a common starting temperature, T_{ref} , such as 293 °K, the data could have been correlated by finding a best fit to one of the Gruneisen equations, which we write in the form,

$$\frac{L_{\text{ref}} - L_T}{L_{\text{ref}}} = \frac{U_{\text{ref}} - U_T}{a[1 - b(U_T - U_0)]}$$

Here U is internal energy, and a and b are constants to be evaluated by fitting the equation to the data. However this is a laborious procedure due to the necessity of constructing in advance a complete table of U versus T for each substance. Consequently a quicker procedure was adopted in many cases, which consisted of smoothing and interpolating graphically down to about 90 °K and using the Gruneisen relation only at lower temperatures. Here the term, $b(U_T - U_0)$, is negligible, and internal energy can be replaced by enthalpy. The latter quantity had already been tabulated by us as part of another compilation. The constant, a , can then be determined from any single value of length change below about 90 °K, such as, from 90 to 20 °K. By differentiation, a is also the constant of proportionality between dL/LdT and C_P . The error resulting from these simplifications of the formula is appreciable only for soft substances of high atomic weight, e.g., lead, indium, mercury. A more serious error is indicated by recent experiments and refinements of theory showing that some variation in the constant, a , will generally occur at temperatures lower than about one third of the Debye temperature. See, for example, Barron [1955], Bijl and Pullan [1954, 1955], Dheer and Surange [1958], Figgins, Jones, and Riley [1956], Gibbons [1958], Rubin, Altman, and Johnston [1954], Simmons and Balluffi [1957]. Because of this effect, the values interpolated by means of the formula are accurate only to one or two figures. Also there is a lower limit to the applicability of the formula. This is the temperature below which the linear term in

the specific heat due to electrons is appreciable. Mikura [1941] and Visvanathan [1951] have shown that a corresponding linear term in dL/LdT should appear, but the coefficient of this term has been calculated only for the free-electron case.

Anomalies in the thermal expansion may occur for various reasons. In fact, dilatometry is a useful tool for exploring solid-state transformations. Some examples of substances showing low temperature anomalies are Dy (ferromagnetic Curie point), KH_2PO_4 (ferroelectric Curie point), MnO (anti-ferromagnetic transformation or Neel point), N_2 (first order phase change), CH_4 (rotational transition) and soft rubbers ("glass" transition).

Articles by Bijl [1957], Gruneisen [1926], and Hume-Rothery [1945] may be consulted for general background on the representation of thermal expansion.

Published thermal expansion data vary greatly in precision. Some papers show as many as five significant figures in $\Delta L/L$ and four in the derivative. However, comparisons between careful investigations on the same pure materials indicate that absolute accuracies better than one percent are seldom attained.

Descriptions of dilatometric techniques will be found in many of the articles selected as "Sources of Data." In addition the bibliography contains selected articles prefixed (T) which are devoted solely to techniques.

The assistance of Vincent D. Arp, Mrs. Marjorie Fewlass, and W. R. Slinkman is gratefully acknowledged.

TABLE 1. List of substances

Elements (See table 2.1)	Alloys (See table 2.2)	Other inorganics (See table 2.3)
Aluminum	Aluminum 2024-T4 ^a	Carbolloy ^b
Antimony	Aluminum 7075-T6 ^a	Carbon dioxide
Beryllium	Aluminum 25 ^b	Glasses:
Bismuth	Aluminum bronze	Optical (misc.) ^c
Cadmium	Beryllium copper	Pyrex
Carbon (diamond)	Brass	Silica
Carbon (graphite)	Bronze ^b	Ice
Chromium	Cast alloys (misc.) ^b	Indium antimonide
Copper	Cast iron ^b	Quartz
Germanium	Constantan	Magnesium oxide
Gold	Contracid	
Indium	German silver	Plastics and elastomers (See table 2.4)
Iron	Inconel	Araldite
Lead	Inconel-X ^a	Catalin
Magnesium	Invar	Dynakon
Manganese	Magnesium AN-M-29 ^a	Fluorothene
Mercury	Monel	Kel-F
Molybdenum	K-Monel ^a	Laminac
Nickel	Soft solder (50 Pb 50 Sn)	Lucite
Niobium ^d	Steels:	Nylon
Palladium	SAE 1010 ^a	Panelyte
Platinum	SAE 1020	Plexiglas
Rhodium	SAE 1095	Polystyrene
Silicon	SAE 6150 ^b	Polythene
Silver	SAE 52100	Rubber:
Sodium	AISI 301	Hard
Tantalum	AISI 302	Silastic 160
Tin	AISI 304	Selectron
Titanium	AISI 310	Teflon
Tungsten	AISI 316	Tenite
Zinc	AISI 322	Vinylite
	AISI 330	
	AISI 347	
	AISI 410	
	Miscellaneous ^b	
	Titanium RC-130-B	
	Titanium Ti-150-A	

^a See table 3.2.
termed Columbium.

^b See table 3.1.

^c See table 3.3.

^d Also

TABLE 2.1. Linear thermal contraction and coefficients of linear thermal expansion

Elements

T	Aluminum		Antimony ^b		Beryllium ^b		Bismuth ^b		Cadmium ^b	
	$10^3 \frac{L_{293} - L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293} - L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293} - L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293} - L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293} - L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$
<i>deg K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>
0	^a 415	0	^a 250	0	^a 131	0	^a 323	0	^a 733	0
10	^a 415	^a 0.05	^a 250	^a 0.1			^a 323	^a 1.1	^a 733	^a 1.1
20	415	.2	^a 250	^a .8	^a 131	^a .01	321	^a 3.4	729	^a 6.2
30	414	.9	^a 248	^a 2.4	^a 131	^a .03	316	^a 6.1	^a 720	^a 11.6
40	413	2.2	^a 245	^a 4.1	^a 131	^a .07	309	7.8	^a 706	^a 15.8
50	410	3.8	^a 240	^a 5.6	^a 131	^a .13	300	9.1	^a 689	^a 19.0
60	405	5.5	^a 234	^a 7.0	^a 131	^a .2	291	10.0	^a 669	^a 21.4
70	399	7.4	^a 226	^a 7.9	^a 130	^a .4	280	10.7	^a 646	^a 23.2
80	391	9.1	218	8.5	^a 130	^a .6	269	11.2	^a 622	^a 24.6
90	381	10.7	209	8.9	129	^a .9	258	11.6	597	25.6
100	370	12.2	200	9.3	128	1.3	246	11.9	571	26.4
120	343	14.6	181	9.7	124	2.2	222	12.2	517	27.8
140	312	16.5	162	10.0	119	3.4	198	12.5	460	28.7
160	277	17.9	142	10.2	111	4.7	173	12.7	402	29.3
180	240	19.0	121	10.4	100	5.9	147	12.8	343	29.7
200	201	20.0	100	10.5	87.3	7.1	121	12.9	284	30.0
220	160	20.8	78.9	10.6	72.0	8.2	95.5	13.0	223	30.2
240	118	21.5	57.5	10.7	54.6	9.2	69.4	13.1	163	30.4
260	75	22.1	35.9	10.8	35.2	10.1	43.3	13.1	102	30.6
273	45	22.5	21.8	10.9	21.8	10.6	26.2	13.1	61.9	30.8
280	30	22.7	14.2	10.9	14.3	10.8	17.1	13.1	40.3	30.9
293	0	23.0	0.0	10.9	0.0	11.2	0.0	13.1	0.0	31.1
300	-16	23.2	-7.7	11.0	-7.9	11.4	-9.2	13.1	-21.8	31.2
Sources of above data	Altman, Rubin, and Johnston 1954		Erfiling 1939		Erfiling 1939 Hidnert and Sweeney 1927		Erfiling 1939		Gruneisen and Goens 1924	
Other refs.	Ayrce 1905 Bijl and Pullan 1955 Buffington and Latimer 1926 Ebert 1928 Figgins, Jones, and Riley 1956 Gibbons 1958 Henning 1907 Hordon, Lement, and Averbach 1953 Hume-Rothery and Strawbridge 1947 Lindemann 1911 Nix and MacNair 1941 Shearer 1905		Dorsey 1907 Gruneisen 1910		Head and Laquer 1952		Dorsey 1907 Gruneisen 1910 Jacobs and Goetz 1937 Wunnenberg, Fischer, and Sapper 1930		Borelius and Johansson 1924 Dorsey 1907 Gruneisen 1910 McLennan and Monkman 1929	

^a Estimated using Gruneisen correlation as explained in Introduction.^b Anisotropic. The above values were calculated from the relation, Mean Value = $\frac{1}{2}(\parallel) + \frac{1}{2}(\perp)$, where (\parallel) and (\perp) signify the same property measuredparallel and perpendicular, respectively, to the trigonal (Sb, Bi) or hexagonal (Be, Cd) axis. See table 4 for representative values of the (\parallel) and (\perp) expansions.

TABLE 2.1. Linear thermal contraction and coefficients of linear thermal expansion—Continued

<i>T</i>	Carbon ^a (diamond ^b)		Chromium ^d		Copper		Germanium		Gold	
	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$
	<i>deg K</i>	<i>deg⁻¹ K</i>	<i>deg K</i>	<i>deg⁻¹ K</i>	<i>deg K</i>	<i>deg⁻¹ K</i>	<i>deg K</i>	<i>deg⁻¹ K</i>	<i>deg K</i>	<i>deg⁻¹ K</i>
0	^a 24.3	0	^a 98.5	0	^a 326	0	^a 92	0	^a 324	0
10	^a 24.3	^a 0.00004			^a 326	^a 0.04				
20	^a 24.3	^a .0003	^a 98.5	^a .03	326	1.3			323	^a 2.4
30	^a 24.3	^a .0008	^a 98.4	^a .09	325	1.0			^a 319	^a 4.8
40	^a 24.3	^a .002	^a 98.3	^a .2	324	2.3	92.2	.07	^a 313	^a 6.7
50	^a 24.3	^a .004	^a 97.9	^a .5	321	3.8	92.1	.20	^a 306	^a 8.2
60	^a 24.3	^a .007	97.3	.84	316	5.5	91.9	.39	^a 297	^a 9.2
70	^a 24.2	^a .01	96.2	1.27	310	7.0	91.4	.67	^a 288	^a 10.0
80	^a 24.2	^a .02	94.7	1.75	302	8.4	90.5	1.05	278	^a 10.6
90	^a 24.1	^a .03	92.7	2.19	293	9.5	89.3	1.54	267	11.1
100	^a 24.0	^a .04	90.3	2.59	283	10.5	87.4	2.20	256	11.5
120	^a 23.7	^a .08	84.5	3.25	260	12.0	81.9	3.25	233	12.1
140	23.1	.14	77.4	3.8	235	13.2	74.9	3.91	208	12.5
160	22.1	.21	69.3	4.3	208	14.1	67.0	4.29	182	12.8
180	20.6	.30	60.3	4.7	179	14.7	58.3	4.58	156	13.1
200	18.6	.40	50.5	5.1	149	15.2	48.7	4.82	129	13.3
220	16.0	.52	40.0	5.4	118	15.6	39.0	5.03	102	13.5
240	12.6	.65	29.1	5.5	87	15.9	28.9	5.23	74.4	13.7
260	8.5	.78	18.0	5.6	55	16.2	18.3	5.42	47.0	13.9
273	6.9	.87	10.7	5.6	33	16.4	11.3	5.53	27.8	14.0
280	3.7	.92	6.9	5.5	22	16.5	7.4	5.59	18.7	14.0
293	0.0	1.0	0.0	5.1	0	16.7	0.0	5.67	0.0	14.1
300	-2.1	1.1	-3.5	5.0	-11	16.8	-4.0	5.75	-10.2	14.1
Sources of above data	Thewlis and Davey 1956		Erfing 1939		Rubin, Altman, and Johnston 1954		Gibbons 1958		Ebert 1928 Nix and MacNair 1941	
Other refs.	Cohen and Olie 1910 Rontgen 1912		Disch 1921 Finc, Greiner and Ellis 1951 Hidnert 1941		Adenstedt 1936 Aoyama and Ito 1939 Beenakker and Swenson 1955, Bijl and Pullan 1955 Borellus and Johansson 1924 Buffington and Latimer 1926 Dorsey 1907 Fraser and Hollis-Hallett 1955 Henning 1907 Kcesom, van Agt, and Jansen 1926 Keyston, MacPherson, and Guptill 1959 Krupkowski and de Haas 1928 Lindemann 1911 Nix and MacNair 1941 Simmons and Balluffi 1957 Simon and Bergmann 1930		Fine 1953 McSkimin 1953 Nitka 1937		Dorsey 1907, 1908 Gruneisen 1910	

^a Estimated using Gruneisen correlation as explained in Introduction.^b The above values are for "gem quality" diamond. Thewlis and Davey also measured industrial diamond but obtained an anomalous minimum near 0° C. Following are some selected values of $10^6(dL/LdT)$ for their industrial diamond: 175° K 0.7, 200° K 0.6, 260° K -0.1 (min), 300° K +0.3.^c Graphite lattice parameters have been measured at low temperatures by Baskin and Meyer [1955] and by Walker, McKinstry, and Wright [1953]. The largest value reported for any of the expansion coefficients was 29×10^{-4} deg⁻¹ K and was for the translaminar direction at 77° K and above. Expansions parallel to the laminae were too small to detect. In addition fragmentary and discordant macroscopic measurements lying within the above limits have been reported by Cohen and Olie [1910], Dewar [1902], and Erfing [1939]. Hidnert [1934] systematically measured the macroscopic expansions ofseveral polycrystalline artificial graphites and obtained values of $10^6(dL/LdT)$ at room temperature ranging from 0.6 to 4. The latter values define the probable range of commercial bonded graphites. These values would be expected to trend toward zero with decreasing temperature.^d Hidnert found that the density and expansion coefficient of new electrolytic chromium were unstable. This was attributed to the large initial hydrogen content. The metal is stabilized by annealing. The table is based on the more pure of two vacuum-annealed samples measured by Erfing. The results with the less pure sample were about 10% higher. There was a minimum in the expansion coefficient at room temperature. This anomaly has been confirmed by Fine et al., and coincides with the antiferromagnetic transition (Neel point) found by Corliss, Hastings, and Weiss [1959].

TABLE 2.1. Linear thermal contraction and coefficients of linear thermal expansion—Continued

Elements

<i>T</i>	Indium ^c		Iron		Lead ^b		Magnesium ^e		α -Manganese ^d		β -Manganese ^e	
	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$
<i>deg K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>
0	^a 706	0	^a 198	0	^a 708	0	^a 490	0				
5					708	0.3						
10	^a 706	^a 2			707	3.2	^a 490	^a 0.05				
20	701	7	198	^a 0.1	700	^a 11	490	^a 4				
30	691	13	^a 198	^a 3	^a 686	^a 17	^a 489	^a 1.4				
40	676	17	^a 197	^a 7	^a 667	^a 20	^a 486	^a 3.3				
50	658	19.1	^a 196	^a 1.3	^a 646	^a 22	^a 482	^a 5.7				
60	638	20.4	^a 195	^a 2.0	^a 624	^a 23	^a 475	^a 8.1				
70	617	21.5	^a 192	^a 2.8	^a 601	^a 24	^a 466	^a 10.3				
80	595	22.4	^a 189	^a 3.5	^a 577	^a 24	454	12.2	380			
90	572	23.2	185	4.2	552	25	441	13.9	372	9.8	420	
100	549	23.9	181	4.9	528	25	427	15.4	361	11.9	406	14.6
120	500	25.2	170	6.3	477	25.6	393	17.6	334	14.4	375	17.0
140	448	26.3	156	7.6	425	26.3	356	19.4	304	16.0	339	18.5
160	394	27.2	140	8.6	372	26.8	316	21.0	271	17.3	301	19.7
180	339	27.9	122	9.4	318	27.2	273	22.2	235	18.4	260	20.7
200	282	28.6	102	10.0	263	27.5	227	23.2	197	19.4	218	21.6
220	224	29.3	82	10.5	208	27.8	180	23.9	158	20.3	174	22.4
240	165	30.1	60	10.9	152	28.2	132	24.4	116	21.0	128	23.2
260	104	30.8	38	11.3	96	28.5	82.9	24.8	73.5	21.8	81.3	24.0
273	63	31.3	23	11.4	58	28.8	50.4	25.1	44.9	22.2	49.9	24.5
280	42	31.5	15	11.5	38	28.9	32.9	25.2	29.3	22.4	32.6	24.8
293	0	32.0	0	11.6	0	29	0.0	25.4	0.0	22.7	0.0	25.4
300	-22	32.2	-8	11.7	-20	29	-17.8	25.5	-16.0	22.9	-17.9	25.7
Sources of above data	Swenson 1955		Ebert 1928 Nix and MacNair 1941		Dheer and Surange 1958 Ebert 1928 Nix and MacNair 1942 Olsen and Rohrer 1957		Ebert 1928 Goens and Schmid 1936 Head and Laquer 1952		Erfiling 1940		Erfiling 1939	
Other refs.	Graham, Moore, & Raynor 1955 Hidnert and Blair 1943		Adenstedt 1936 Dorsey 1907 Owen and Williams 1954 Simon and Bergmann 1930		Dorsey 1908 Gruneisen 1910 Head and Laquer 1952 Lindemann 1911 McLennan, Allen, and Wilhelm 1931		Gruneisen 1910 Hidnert and Sweeney 1928		Disch 1921			

^a Estimated using Gruneisen correlation as explained in Introduction.^b Superconducting lead has a slightly greater volume and a slightly smaller expansion coefficient than normal lead according to data by Olsen and Rohrer covering the region from 1 to the transition temperature, 7.2 °K. For example, the difference in expansion coefficients at 5 °K is about 10%.^c Anisotropic. The above values were calculated from the relation, Mean Value = 1/3(\parallel) + 2/3(\perp), where (\parallel) and (\perp) signify the same property measured parallel and perpendicular, respectively, to the hexagonal axis. See table 4 for representative values of the (\parallel) and (\perp) expansions.^d α -Mn is the form that is stable at low temperatures. It has an antiferromagnetic transition at about 95 °K which would make extrapolation of the above values uncertain.^e β -Mn is stable between 730 and about 1100 °C. Erfiling's sample was prepared by quenching from 1100 °C in vacuum. There were insufficient specific heat data to make a reliable extrapolation below 90 °K.^f Anisotropic, tetragonal. Graham, Moore, and Raynor gave values of the lattice parameters down to 90 °K that show great anisotropy in the thermal expansion. Their low temperature data are not sufficiently accurate or detailed to serve as the basis of an extended table of values, so the more extensive data of Swenson on a polycrystalline sample were used. The contractions tabulated above are about 8% smaller than the average linear contractions derivable from the data of Graham, Moore, and Raynor. The data of Hidnert and Blair, also on a polycrystalline sample, are still smaller.

TABLE 2.1. Linear thermal contraction and coefficients of linear thermal expansion—Continued

Elements

T	γ -Manganese ^b		Mercury ^c		Molybdenum		Nickel		Niobium ^e		Palladium	
	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{234}-L_T}{L_{234}}$	$10^6 \frac{dL}{L_{234} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$
<i>deg K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>
0	^a 257	0	^a 844	0	^a 95	0	^a 224	0	^a 143	0	^a 241	0
10			^a 841	^a 7	^a 94.9	^a 0.01						
20	^a 257	^a 0.3	^a 830	^a 15	^a 94.8	^a .06	224	^a 0.2	^a 143	^a 0.3	^a 241	^a 0.5
30	^a 256	^a 0.7	^a 812	^a 21	^a 94.7	^a .2	^a 224	^a .5	^a 143	^a 0.9	^a 240	^a 1.3
40	^a 255	^a 1.4	^a 788	^a 26	^a 94.4	^a .5	^a 223	^a 1.0	^a 141	^a 1.7	^a 238	^a 2.5
50	^a 253	^a 2.4	^a 760	^a 29	^a 93.8	^a .8	^a 221	^a 1.9	^a 139	^a 2.4	^a 235	^a 3.8
60	^a 250	^a 3.5	^a 730	^a 31	^a 92.7	^a 1.2	^a 219	^a 2.8	^a 137	^a 3.1	^a 231	^a 4.9
70	^a 246	^a 4.5	^a 697	^a 33	^a 91.3	^a 1.7	^a 216	^a 3.8	^a 133	^a 3.6	^a 225	^a 5.9
80	^a 241	^a 5.5	663	^a 34.5	89.4	^a 2.1	211	^a 4.7	129	4.0	^a 219	^a 6.7
90	^a 235	^a 6.3	628	35.9	87.1	2.48	206	5.5	125	4.4	211	7.4
100	^a 228	^a 7.2	592	37.0	84.4	2.80	201	6.1	121	4.7	204	8.1
120	^a 213	^a 8.5	516	38.8	78.2	3.39	187	7.5	111	5.2	187	9.0
140	^a 194	^a 9.7	437	40.2	71.1	3.77	171	8.8	99.4	5.6	168	9.7
160	^a 174	^a 10.6	355	42.1	63.2	4.13	152	9.8	87.7	5.9	148	10.2
180	^a 152	^a 11.5	268	44.6	54.6	4.42	132	10.5	75.5	6.2	127	10.7
200	128	12.3	176	47.8	45.6	4.63	111	11.0	63.0	6.4	105	10.9
220	103	13.0	76	52.2	36.2	4.78	88	11.5	50.0	6.6	83.3	11.2
230			22	55.3								
^d 234			0	57.2								
240	76.2	13.7			26.5	4.89	65	11.9	36.7	6.7	60.8	11.3
260	48.3	14.2			16.6	4.98	41	12.2	23.1	6.8	38.0	11.4
273	29.6	14.6			10.1	5.02	25	12.3	14.1	6.9	23.1	11.5
280	19.3	14.7			6.6	5.04	16	12.4	9.2	6.9	15.0	11.5
293	0.0	15.0			0.0	5.07	0	12.6	0.0	7.0	0.0	11.6
300	-10.6	15.1			-3.6	5.09	-9	12.6	-5.0	7.0	-8.1	11.6
Sources of above data	Erfiling 1940		Carpenter and Oakley 1931 Hill 1935		Erfiling 1939 Nix and MacNair 1942		Krupkowski and deHaas 1928 Nix and MacNair 1941		Erfiling 1942		Nix and MacNair 1942	
Other refs.			Dewar 1902 Gruncisen and Seckell 1934 Sapper and Biltz 1931		Disch 1921 Schad and Hidnert 1919		Adenstedt 1936 Altman, Rubin, and Johnston 1954 Aoyama and Ito 1939 Chcvenard 1926 Disch 1921 Henning 1907 Simon and Bergmann 1930		Hidnert and Krider 1933		Henning 1907 Scheel 1907	

^a Estimated using Gruncisen correlation as explained in Introduction.^b γ -Mn is a ductile form that is stable between about 1100 and 1135 °C when pure. It is often found as a separate phase in manganese alloys. Erfiling's sample was produced by electrolytic deposition.^c Anisotropic. The above values were calculated from the relation, MeanValue = $\frac{1}{2}(\parallel) + \frac{3}{2}(\perp)$, where (\parallel) and (\perp) signify the same property measured parallel and perpendicular, respectively, to the trigonal axis. See table 4 for representative values of the (\parallel) and (\perp) expansions.^d Melting point of mercury.^e Also termed columbium.

TABLE 2.1. Linear thermal contraction and coefficients of linear thermal expansion—Continued

Elements

T	Platinum		Rhodium		Silicon		Silver		Sodium ^b	
	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$
deg K		deg ⁻¹ K		deg ⁻¹ K		deg ⁻¹ K		deg ⁻¹ K		deg ⁻¹ K
0	^a 195	0	^a 160	0	^a 22	0	^a 413	0	^a 1430	0
10	^a 195	^a 0.08					^a 413	^a 0.1	^a 1430	^a 0.7
20	^a 195	^a 0.5	^a 160	^a 0.09			412	^a 1	^a 1430	^a 5
30	^a 194	^a 1.5	^a 160	^a .4			^a 410	^a 3	^a 1420	^a 11
40	^a 192	^a 2.6	^a 159	^a .9	21.6	-0.05	^a 405	^a 6	^a 1400	^a 17
50	^a 189	^a 3.8	^a 158	^a 1.7	21.7	- .20	^a 398	^a 8	^a 1380	^a 23
60	^a 185	^a 4.7	156	^a 2.5	22.0	- .41	^a 389	^a 10	^a 1360	^a 29
70	^a 180	^a 5.4	153	3.2	22.5	- .59	^a 378	^a 12	^a 1330	^a 33
80	^a 174	^a 6.0	149	3.9	23.2	- .77	366	^a 13	1290	^a 38
90	168	6.5	145	4.5	24.0	- .51	353	13.6	1250	42.4
100	161	6.8	140	5.0	24.3	- .31	339	14.6	1210	46.3
120	147	7.3	129	5.9	24.7	+ .01	308	15.9	1110	52.4
140	132	7.7	117	6.5	24.3	.31	276	16.5	998	56.9
160	116	8.0	104	6.9	23.4	.65	242	16.9	881	60.4
180	99.4	8.3	89.3	7.3	21.7	1.05	208	17.3	757	63.1
200	82.4	8.5	74.5	7.6	19.1	1.49	173	17.7	629	65.2
220	65.0	8.6	59.1	7.8	15.9	1.83	137	18.1	497	66.7
240	47.5	8.7	43.4	8.0	11.8	2.07	100	18.5	363	67.8
260	29.6	8.8	27.2	8.1	7.8	2.22	63	18.8	227	68.4
273	18.0	8.8	16.6	8.2	4.8	2.28	38	19.0	137	68.6
280	11.6	8.9	10.8	8.3	3.3	2.30	25	19.1	89.4	68.7
293	0.0	8.9	0.0	8.4	0.0	2.32	0	19.2	0.0	68.8
300	-6.4	8.9	-5.9	8.4	-1.4	2.33	-13	19.3	-48.2	68.8
Sources of above data	Nix and MacNair 1942		Erfing 1939 Valentiner and Wallot 1915		Gibbons 1958		Ebert 1928 Nix and MacNair 1942		Siegel and Quimby 1938	
Other refs.	Dorsey 1907 Henning 1907 Onnes and Clay 1906 Scheel 1907 Scheel and Heuse 1907 Valentiner and Wallot 1915		Head and Laquer 1952		Erfing 1942 Fine 1953 Simon and Bergmann 1930 Valentiner and Wallot 1915		Ayres 1905 Buffington and Latimer 1926 Dorsey 1907 Henning 1907 Keesom and Jansen 1927 Keesom and Kohler 1933 Lindemann 1911 Owen and Williams 1954 Shearer 1905		Barrett 1956 Dewar 1902 Swenson 1955	

^a Estimated using Gruneisen correlation as explained in Introduction.^b It has recently been shown (Barrett 1956, Hull and Rosenberg 1959) that sodium partially transforms at low temperatures from the normal body-centered cubic structure to close-packed hexagonal. The transformation is of the martensitic type and is promoted by cold-working at the low temperatures. The above values include an extrapolation downwards from the

region where the bcc structure is stable. The effect of the transformation on the thermal expansion is not known, but is small, inasmuch as Barrett found the densities of the two forms at 5 °K to be the same within his experimental uncertainty. The fit of the Gruneisen relation to the data was not very satisfactory, and hence there is not much confidence in the extrapolated values above.

TABLE 2.1. Linear thermal contraction and coefficients of linear thermal expansion—Concluded

Elements

<i>T</i>	Tantalum		Tin ^a (white) ^b		Titanium ^d		Tungsten		Zinc ^c	
	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$
<i>deg K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>
0	^a 143	0	^a 447	0	^a 151	0	^a 85.8	0	^a 683	0
10	^a 143	^a 0.05	^a 447	^a 0.7			^a 85.8	^a 0.007	^a 683	^a 0.3
20	^a 143	^a 0.4	^a 445	^a 3	151	^a 0.08	^a 85.8	^a .06	^a 682	^a 3
30	^a 142	^a 1.1	^a 441	^a 6	151	^a .3	^a 85.7	^a .2	^a 677	^a 8
40	^a 141	^a 2.0	^a 433	^a 9	150	^a .6	^a 85.3	^a .6	^a 667	^a 13
50	^a 138	^a 2.8	^a 423	^a 11	149	1.2	^a 84.5	^a 1.0	^a 652	^a 17
60	^a 135	^a 3.5	^a 412	^a 12	148	2.0	^a 83.3	^a 1.5	^a 633	^a 21
70	^a 131	^a 4.1	399	^a 13	145	2.7	^a 81.7	^a 1.8	^a 611	^a 22
80	^a 127	^a 4.5	385	14.2	142	3.4	^a 79.7	^a 2.2	^a 588	^a 23
90	122	^a 4.9	371	15.0	139	4.0	^a 77.4	^a 2.4	565	23.6
100	117	5.2	356	15.6	134	4.5	^a 74.8	^a 2.7	541	24.2
120	106	5.5	324	16.4	125	5.3	69.1	3.06	492	25.3
140	95.1	5.8	290	17.1	113	6.0	62.7	3.38	440	26.3
160	83.5	5.9	255	17.7	101	6.5	55.6	3.66	386	27.3
180	71.5	6.0	219	18.2	87.4	6.9	48.1	3.89	331	28.1
200	59.3	6.1	183	18.7	73.2	7.3	40.1	4.07	274	28.7
220	47.0	6.2	145	19.1	58.3	7.6	31.9	4.20	216	29.1
240	34.4	6.3	106	19.5	42.9	7.8	23.4	4.30	157	29.4
260	21.6	6.5	66.7	19.9	27.0	8.0	14.7	4.39	98	29.6
273	13.1	6.5	40.7	20.1	16.5	8.2	8.9	4.44	60	29.7
280	8.5	6.6	26.5	20.3	10.8	8.2	5.8	4.46	39	29.8
293	0.6	6.6	0.0	20.5	0.0	8.3	0.0	4.49	0	29.9
300	-4.6	6.6	-14.4	20.6	-5.9	8.4	-3.2	4.52	-21	30.0
Sources of above data	Nix and MacNair 1942		Erfling 1939		Altman, Rubin, and Johnston 1954 Erfling 1942		Nix and McNair 1942		Gruneisen and Goens 1924	
Other refs.	Disch 1921 Hidnert 1929		Cohen and Olie 1910 Dorsey 1907 Gruneisen 1910		Head and Laquer 1952 Hidnert 1943		Disch 1921 Hidnert and Sweeney 1925		Borelius and Johansson 1924 Dorsey 1908 Gruneisen 1910 Head and Laquer 1952 Lindemann 1911 McLennan and Monkman 1929	

^a Estimated using Gruneisen correlation as explained in Introduction.^b Anisotropic. The above values were calculated from the relation, Mean Value = $\frac{1}{2}(\parallel) + \frac{1}{2}(\perp)$, where (\parallel) and (\perp) signify the same property measured parallel and perpendicular, respectively, to the tetragonal axis. See table 4 for representative values of the (\parallel) and (\perp) expansions.^c Thewlis and Davey (1954) measured the lattice parameter of *grey tin*, a brittle form with diamond-type lattice that is stable below 18° C. Their data cover the range, -130 to +20 °C, and are represented by a constant expansion coefficient, $dL/LdT = 4.7 \times 10^{-6}$ deg⁻¹ C. See also Cohen and Olie (1910). The ordinary ductile variety (white tin) if pure may transform to grey tin at low ambient temperatures but is stabilized by impurities.^d Titanium, having hexagonal crystal structure, should expand anisotropically. However, no lattice parameter or single crystal measurements are available to indicate the magnitude of this effect at low temperatures. The above data at 100 °K or higher are based on an average of two strips cut by Erfling perpendicular to one another from a rolled sheet. Although Altman et al., and Head and Laquer both measured samples from hot stock of un-

known history, their results were within 3% of Erfling's average values, thus indicating that effects due to preferred orientation are small. The largest effect of this kind was shown by a wire measured by Erfling. Its axial expansion was as much as 13% greater than the above values. The table values below 100 °K are based on Altman et al.

^e Anisotropic. The above values were calculated from the relation, Mean Value = $\frac{1}{2}(\parallel) + \frac{1}{2}(\perp)$, where (\parallel) and (\perp) signify the same property measured parallel and perpendicular, respectively to the hexagonal axis. See table 4 for representative values of the (\parallel) and (\perp) expansions. The data on polycrystalline zinc are discordant. Thus the expansion coefficients of Dorsey and of Head and Laquer are as much as 20% lower than values above, while those of Gruneisen and of Lindemann are less than one-third as great. These differences are attributable to the exceptional anisotropy of zinc combined with uncontrolled preferred orientation of the crystallites. It is evidently difficult to prevent such preferred orientation, and the expansions of various samples of polycrystalline zinc could conceivably cover a wide range of values between the limits set by the (\parallel) and (\perp) values.

TABLE 2.2. Linear thermal contraction and coefficients of linear thermal expansion

Alloys

T	Aluminum bronze ^b		Beryllium copper ^c		Brass, yellow ^d		Constantan ^e		Conradid ^f		German silver ^g	
	$10^3 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^3 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$
<i>deg K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>
0			^a 316	0	^a 384	0			^a 232	0	^a 376	0
10			316	^a 0.04	^a 384	^a 0.1			^a 232	^a 0.01	^a 376	^a 0.2
20			316	^a .09	383	^a .5	269		232	^a .06	^a 376	^a .5
30			316	^a .5	382	^a 1.8			232	^a .3	375	1.3
40			315	1.4	380	3.7			231	^a .9	373	3.2
50			313	2.7	375	5.8			230	1.8	369	5.1
60			309	4.3	368	7.6	258	4.6	228	2.8	362	6.8
70			304	6.5	360	9.2	253	5.6	224	3.9	354	8.4
80			296	8.4	350	10.6	247	6.6	220	5.0	345	9.7
90	265	9	287	9.6	339	11.8	240	7.5	214	5.9	335	10.8
100	255	10	277	10.4	326	12.9	232	8.3	208	6.8	323	11.8
120	235	11	255	11.6	299	14.4	214	9.6	193	8.2	298	13.6
140	213	11	231	12.4	269	15.4	194	10.6	176	9.3	269	14.9
160	189	12	206	13.2	237	16.3	172	11.4	156	10.2	238	15.9
180	164	13	179	13.8	204	16.9	148	12.1	135	10.8	205	16.7
200	137	14	151	14.5	169	17.4	124	12.6	113	11.3	170	17.3
220	110	14	121	15.2	134	17.8	98.1	13.0	90.2	11.7	135	17.8
240	81	15	90	16.0	98.4	18.1	71.8	13.3	66.4	12.1	99	18.1
260	51	15	57	16.7	61.8	18.5	45.0	13.5	41.9	12.4	62	18.3
273	^a 32	^a 16	35	17.2	37.3	18.7	27.3	13.6	25.4	12.6	37	18.5
280	^a 21	^a 16	23	17.4	24.6	18.8	17.8	13.7	16.9	12.8	24	18.5
293	^a 0	^a 16	0	17.9	0.0	19.0	0.0	13.7	0.0	13.0	0	18.6
300	^a -11	^a 16	-13	18.1	-13.3	19.1	-9.6	13.8	-9.1	13.1	-13	18.6
Sources of above data	Fontana 1948		Beenakker and Swenson 1955		Altman, Rubin, and Johnston 1954		Aoyama and Ito 1939 Krupkowski and deHaas 1928		Altman, Rubin, and Johnston 1952		Beenakker and Swenson 1955	
Other refs.	Jaffee and Ramsey 1948				Beenakker and Swenson 1955 Fraser and Hollis-Hallet 1955 Henning 1907 Keyston, MacPherson, and Guptill 1959		Henning 1907 Krupkowski 1929					

^a Estimated^b 9 Al, \approx 1 Fe, 0.5 Ni, 0.5 Sn, bal. Cu. The accuracy of the original data is estimated as not better than $\pm 10\%$. Jaffee and Ramsey give data above 170 °K for three compositions in various physical conditions.^c 2 Be, 0.3 Co, bal. Cu (BERYLCO 25). Originally half-hard, then heat treated for 2 hours at 200 °C. No observable difference was found in the thermal expansions for the two states of hardness.^d 65 Cu, 35 Zn.^e 50 Cu, 50 Ni. The name Constantan is applied to binary alloys in the range, 60 to 45 Cu, 40 to 55 Ni. The most common composition is 55 Cu, 45 Ni. The above expansion data should represent all Constantans within a few percent. Small expansion anomalies of magnetic origin occur in this system. The ferromagnetic Curie points range from about 0 °K for 40% Ni to roughly 150 °K for 55% Ni.^f 60 Ni, 15 Cr, 16 Fe, 7 Mo.^g Composition unknown. The compositions of alloys known by this name usually lie within the limits, 45 to 62 Cu, 10 to 30 Ni, 20 to 35 Zn.

TABLE 2.2. Linear thermal contraction and coefficients of linear thermal expansion—Continued

Alloys

<i>T</i>	Inconel ^b		Invar ^c		Monel ^d		Soft solder ^e		Steel, SAE 1020 ^f		Steel, SAE 1095 ^g	
	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6 dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6 dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6 dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6 dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6 dL}{L_{293} dT}$	
<i>deg K</i>		<i>deg⁻¹ K</i>			<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>	
0	^a 229	0	^a 52	^a 251	0			^a 202	0			
10	^a 229		52	^a 251	^a 0.03							
20	229	^a 0.03	52	251	^a 2			202	^a 0.1			
30	229	.3	52	251	.6			201	.3			
40	228	1.0	52	250	1.4			201	.8			
50	227	1.9	52	248	2.3			200	1.4			
60	224	2.8	52	245	3.4			198	2.3			
70	221	3.8	51	241	4.6			195	3.1			
80	217	4.8	50	236	5.7			192	4.0	213	6.7	
90	211	5.7	49	230	6.7	467	19.6	187	4.8	206	6.9	
100	205	6.5	47	223	7.5	447	20.0	182	5.5	199	7.2	
120	191	7.9	43	206	8.9	407	20.7	170	6.8	184	7.8	
140	174	9.1	39	187	9.9	365	21.4	155	7.8	168	8.3	
160	154	10.0	34	167	10.8	321	22.2	138	8.7	151	8.9	
180	134	10.7	29	144	11.5	276	22.9	120	9.4	132	9.8	
200	112	11.2	23	121	12.0	229	23.5	101	9.9	112	10.4	
220	89.1	11.6	18	96.4	12.5	182	24.1	80.7	10.4	90.5	11.3	
240	65.6	12.0	14	70.9	12.9	133	24.6	59.6	10.8	67.1	12.0	
260	41.4	12.3	8.6	44.7	13.3	83	25.0	37.7	11.1	42.5	12.6	
273	25.2	12.5	5.2	27.1	13.5	51	25.2	22.9	11.4	26.0	12.8	
280	16.6	12.6	3.4	15.1	13.6	33	25.3	15.1	11.5	17.0	12.9	
293	0.0	12.9	0	0.0	13.8	0	25.4	0.0	11.7	0.0	13.2	
300	-9.0	13.0	-1.8	-9.7	13.9	-18	25.5	-8.3	11.9	-9.3	13.3	
Sources of above data	Altman, Rubin, and Johnston 1952		Beenakker and Swenson 1955		Altman, Rubin, and Johnston 1952		Dorsey 1907		Altman, Rubin, and Johnston 1952		Werner 1924	
Other refs.	Lucks and Deem 1958		Chevenard 1914 Gregg 1954 Masumoto 1934 Molby 1912 Sebeel 1921		Ackerman 1936 Aoyama and Ito 1939 Fraser and Hollis- Hallett 1955 Krupkowski and de Haas 1928				Beenakker and Swen- son 1955 Dorsey 1910 Gregg 1954			

^a Estimated.^b 80 Ni, 14 Cr, 6 Fe.

^c The expansions of the Invar alloys are sensitive to composition and heat treatment [see Metals Handbook, ASM, 1948, pp. 601-5]. The above data are for an alloy believed to be 42 Ni, 0.8 Mn, bal. Fe, annealed [Lloyd B. Nesbitt, private communication]. Although Beenakker and Swenson referred to this as "Invar", this composition approximates the alloy, Dumet, used for sealing to glass. In the iron-nickel alloy system, the minimum value of room temperature expansion coefficient occurs at about 36% Ni.

^d 67 Ni, 30 Cu, 1.5 Fe, "cold-rolled".^e 50 Pb, 50 Sn.

^f 0.18 C, 0.33 Mn, 0.01 Si, bal. Fe. According to Beenakker and Swenson, cast iron had the same thermal expansion as 1020 steel within their experimental uncertainty of $\pm 3 \times 10^{-5}$ in $\Delta L/L$.

^g The above data are the average of two German steels that approximated the specification of SAE 1095. The steels were both "hard" and could be represented by the approximate composition: 1.1 C, 0.2 Si, 0.3 Mn, 0.02 S, 0.03 P. Their expansion coefficients differed from each other by about 10%. The expansion coefficients in the "soft" condition were also measured and were lower than the above values by 10% at 80 °K to 16% at 300 °K.

TABLE 2.2. Linear thermal contraction and coefficients of linear thermal expansion—Continued

Alloys

T	Steel, SAE 52100 ^b		Steel, AISI 301 ^c		Steel, AISI 302 ^d		Steel, AISI 304 ^e		Steel, AISI 310 ^f		Steel, AISI 316 ^g	
	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6}{L_{293}} \frac{dL}{dT}$
<i>deg K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>
0					^a 316	0	^a 296	0			^a 297	0
10					316	^a 0.04	296	^a 0.01			297	^a 0.04
20					316	^a .09	296	.02			297	^a .09
30					316	.5	296	.62			297	.5
40					315	1.4	296	1.1			296	1.4
50					313	2.7	294	2.3			294	2.7
60					309	4.3	291	4.3			290	4.3
70					304	6.5	285	6.1			285	6.5
80	198	6.2			296	8.3	279	7.5			277	8.2
90	192	6.6	267	9.6	287	9.6	271	8.7	246	8.9	269	9.4
100	185	6.9	257	10.1	277	10.4	261	9.6	237	9.1	259	10.2
120	171	7.3	236	11.0	255	11.6	241	10.9	218	9.8	237	11.3
140	156	7.6	213	11.8	231	12.4	218	12.0	198	10.7	214	12.1
160	140	8.2	188	12.5	206	13.2	193	12.8	176	11.4	189	12.7
180	123	8.9	163	13.1	179	13.8	167	13.4	152	12.1	163	13.2
200	105	9.7	136	13.6	151	14.5	139	14.0	127	12.7	136	13.6
220	84.4	10.6	109	14.1	121	15.2	111	14.5	101	13.2	109	14.1
240	62.4	11.3	80.1	14.5	89.6	16.0	81.7	14.9	74.5	13.6	80.1	14.5
260	39.4	11.7	50.5	15.0	57.0	16.7	51.4	15.3	46.9	14.0	50.6	15.0
273	24.0	11.9	30.9	15.3	35.0	17.2	31.4	15.5	28.6	14.2	30.9	15.3
280	15.6	12.0	20.2	15.4	22.9	17.4	20.5	15.6	18.7	14.3	20.2	15.4
293	0.0	12.1	0.0	15.7	0.0	17.9	0.0	15.9	0.0	14.5	0.0	15.7
300	-8.5	12.1	-11.0	15.8	-12.7	18.1	-11.1	16.0	-10.2	14.6	-11.0	15.8
Sources of above data	Werner 1924		Furman 1950		Beenakker and Swenson 1955		Altman, Rubin, and Johnston 1954 Beenakker and Swenson 1955		Furman 1950		Beenakker and Swenson 1955	
Other refs.			Lucks and Deem 1958				Fontana 1948 Fontana, Bishop, and Spretnak 1953 Furman 1950				Furman 1950 Lucks and Deem 1958	

^a Estimated.

^b The measurements were made on a German steel that approximated the specifications of SAE 52100. Its composition was 0.94 C, 0.27 Si, 0.34 Mn, 0.95 Cr, bal. Fe. The above data adequately represent two "hard" samples, one of which was "heated at 750 °C", the other "quenched from 850 °C in oil and tempered at 630 °C". The expansion coefficients in the "soft" condition were also measured and were about 8% lower than the above values at 80 °K, about the same from 125 to 200 °K, and about 10% lower at 300 °K.

^c 0.13 C, 0.80 Mn, 0.54 Si, 16.9 Cr, 7.25 Ni, bal. Fe. Annealed 30 min at 1950 °F and water quenched. After cooling to 80 °K and rewarming to room temperature a small permanent expansion was found to have occurred due to irreversible formation of ferrite.

^d Composition and heat treatment of sample not stated. Composition limits for this alloy are: 0.05–0.20 C, 2 (max.) Mn, 1 (max.) Si, 17–19 Cr, 8–10 Ni, bal. Fe.

^e Composition limits for this alloy are: 0.08 (max.) C, 2 (max.) Mn, 1 (max.) Si, 18–20 Cr, 8–11 Ni. Altman et al., found small irreversible effects and, below 35 °K, small negative values of expansion coefficient. While we have given their results inferior weight in this region, the effects were undoubtedly real and attributable to martensitic transformation on cooling [Reed and Mikesell, 1958]. In this alloy the extent of transformation that is produced by cooling is sensitive to composition and has been found to vary from zero to about 50% [R. P. Reed, private communication]. Complete transformation would be accompanied by a mean increase in linear dimension of roughly 1% [Ward, Jepson, and Rait, 1952; and Fiedler, Averbach, and Cohen, 1955].

^f 0.11 C, 1.51 Mn, 0.42 Si, 0.01 S, 0.02 P, 27.2 Cr, 21.6 Ni, bal. Fe. Annealed 30 min at 1950 °F and water quenched.

^g Composition and heat treatment of sample not stated. Composition limits for this alloy are: 0.10 (max.) C, 2 (max.) Mn, 1 (max.) Si, 16–18 Cr, 10–14 Ni, 2–3 Mo, bal. Fe.

TABLE 2.2. Linear thermal contraction and coefficients of linear thermal expansion—Concluded

Alloys

<i>T</i>	Steel, AISI 322 ^b		Steel, AISI 330 ^c		Steel, AISI 347 ^d		Steel, AISI 410 ^e		Titanium, RC-130-B ^f		Titanium, Ti-150-A ^g	
	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^6 \frac{dL}{L_{293} dT}$
<i>deg K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>
0							^a 176	0				
20							176	^a 0.06				
30							176	.2				
40							176	.4				
50							175	.9				
60							174	1.6				
70							172	2.4	218	5.0	168	3.9
80							169	3.2	213	5.4	164	4.3
90			208	5.6	262	9.4	165	4.0	208	5.8	159	4.6
100	146	5	202	6.3	253	9.8	161	4.7	202	6.3	154	5.0
120	136	5	188	7.5	233	10.5	150	6.0	187	7.1	143	5.7
140	124	6	172	8.5	211	11.3	138	7.0	172	8.0	131	6.4
160	112	7	154	9.3	187	12.1	123	7.7	155	8.8	118	7.0
180	98	7	135	10.1	163	12.8	107	8.3	137	9.7	103	7.6
200	83	8	114	10.8	136	13.4	89.4	8.8	117	10.6	87	8.2
220	67	8	91.6	11.5	109	14.0	71.4	9.2	95	11.4	71	8.7
240	50	9	68.0	12.1	80.2	14.6	52.6	9.5	71	12.3	53	9.2
260	32	9	43.3	12.7	50.6	15.0	33.2	9.8	46	13.1	34	9.7
273	20	10	26.6	13.0	30.9	15.3	20.3	10.0	28	13.7	21	10.1
280	13	10	17.4	13.2	20.2	15.4	13.2	10.1	19	14.0	14	10.2
293	0	10	0.0	13.6	0.0	15.6	0.0	10.3	0	14.5	0	10.5
300	-7	10	-9.6	13.8	-11.0	15.7	-7.2	10.4	-10	14.8	-7	10.7
Sources of above data	Fontana 1948		Furman 1950		Furman 1950		Altman, Rubin, and Johnston 1952		Bishop, Spretnak, and Fontana 1953 ^h		Bishop, Spretnak, and Fontana 1953 ^h	
Other refs.					Luks and Deem 1958							

^a Estimated.^b 0.07 C, 0.43 Mn, 0.53 Si, 17.0 Cr, 6.5 Ni, 0.12 Al, 0.37 Ti, bal. Fe. "Air cooled from 1900 °F and aged at 1000 °F for 40 min." These data are of a lower order of accuracy than the other data on steels in table 2.2.^c 0.05 C, 1.81 Mn, 0.62 Si, 0.006 S, 0.006 P, 15.3 Cr, 35.2 Ni, bal. Fe. Annealed 30 min at 1950 °F and water quenched.^d 0.07 C, 1.74 Mn, 0.56 Si, 0.006 S, 0.019 P, 18.65 Cr, 11.3 Ni, 0.77 Nb, bal. Fe. Annealed 30 min at 1950 °F and water quenched.^e 0.09 C, 0.32 Mn, 0.36 Si, 0.01 S, 0.01 P, 12.6 Cr, 0.12 Ni, 0.06 Cu, 0.03 N, bal. Fe.^f 0.24 C, 3.8 Mn, 3.8 Al, bal. Ti. Annealed one hr at 1300 °F and air cooled.^g 0.05 (max.) C, 2.7 Cr, 1.3 Fe, 0.08 (max.) N, bal. Ti. Annealed 6 hr at 1200 °F.^h Comparison of measurements in this paper on a commercially pure titanium with data from other sources (see Ti, table 2.1) suggests that the above data on titanium alloys may be grossly inaccurate.

TABLE 2.3. Linear thermal contractions and coefficients of linear thermal expansion

Other inorganic substances *

T	Carbon dioxide		Pyrex	Silica glass ^b	Ice ^c		Indium antimonide		Quartz (crystalline,) ^d		Magnesium oxide	
	$10^4 \frac{L_{190}-L_T}{L_{190}}$	$\frac{10^6 dL}{L_{190} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$10^5 \frac{L_{273}-L_T}{L_{273}}$	$\frac{10^6 dL}{L_{273} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6 dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6 dL}{L_{293} dT}$	$10^5 \frac{L_{293}-L_T}{L_{293}}$	$\frac{10^6 dL}{L_{293} dT}$
<i>deg K</i>		<i>deg⁻¹ K</i>				<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>		<i>deg⁻¹ K</i>
0			a 54.7	a-8							†139	0
10											†139	
20	266	32	55.7	-6.60			83.7	-0.06			†139	†0.02
30	262	49					84.4	-0.10			†139	†0.06
40	256	67	56.7	-4.90			86.2	-1.72			†139	†1.14
							87.2	-0.82			†139	
50	249	83					88.0	-0.33			†139	†2.27
60	240	98	56.2	-3.02			88.2	+0.28			†138	†4.45
70	229	116					87.6	0.89			†138	†8
80	216	132	53.7	-1.41	612	7.7	86.4	1.50			†137	†1.2
90	203	147			603	10.2	84.6	2.18	107	2.7	135	†1.7
100	187	160	50.2	-0.12	592	12.7	82.2	2.76	104	3.1	†133	†2.3
110	171	170										
120	153	177	46.2	+0.87	562	17.7	75.7	3.48	97.7	3.7	†127	†3.4
130	135	184										
140	117	190	41.7	1.61	522	22.7	68.6	3.83	89.8	4.2	†119	†4.6
150	97	197										
160	77	207	37.2	2.08	471	27.7	60.8	4.08	80.9	4.7	109	5.6
170	56	230										
180	31	272	32.2	2.32	411	32.7	52.6	4.27	71.2	5.1	97	6.6
190	0	351										
200			27.2	2.36	341	37.6	43.9	4.43	60.5	5.5	83	7.4
220			21.7	2.18	261	42.6	34.8	4.58	49.1	5.9	67	8.1
240			15.7	1.81	171	47.6	25.6	4.71	36.7	6.4	51	8.8
260			10.2	1.26	70	52.6	16.2	4.83	23.6	6.8	33	9.4
273			6.2	0.81	0	55.8	9.8	4.91	14.6	7.1	20	9.7
280			4.2	0.54			6.5	4.95	9.6	7.2	13	9.9
293			0.0	0.0			0.0	5.01	0.0	7.5	0	10.2
300			-2.3	-0.29			-3.5	5.04	-5.3	7.6	-7	10.3
Sources of above data	Keesom and Kohler 1933-4 Maass and Barnes 1926		Head and Laquer 1952	Keesom and Doborzynski 1934 Scheel and Heuse 1914	Powell 1958		Gibbons 1958		Buffington and Latimer 1926		Durand 1936	
Other refs.	Keesom and Kohler 1933		Buffington and Latimer 1926 Tool and Saunders 1948 Winter-Klein 1950	Beattie et al. 1941 Dorsey 1907 Head and Laquer 1952 Henning 1907 Scheel 1907 Scott 1933 Sosman 1927 Souder and Hihnert 1926 Valentiner and Wallot 1915	Dennison 1921 Dewar 1902 Jakob and Erk 1928 Konig 1944 Lisgarten and Blackman 1956 Lonsdale 1958 Shalleross and Carpenter 1957		Potter 1956		Dorsey 1908 Lindemann 1912 Nix and MacNair 1941 Scheel 1907 Sosman 1927			

* Estimated.

^b The thermal expansion of silica glass (fused silica, vitreous silica, quartz glass), though small, is variable from sample to sample. The above values are thought to be fairly representative of average behavior. The temperature of minimum length can vary from 180 to 230° K. Variations from the above values as large as 2×10^{-3} below 180° K and 50% from 180 to 300° K are possible.

^c According to Powell, ice is slightly anisotropic, the expansion coefficients parallel and normal to the optic axis differing by about 1×10^{-6} deg⁻¹ K. The above values are an average over all directions. The only other ex-

tended investigation [Jakob and Erk] is not in good agreement with Powell and found negative expansion coefficients below about 70° K.

^d Measured parallel to the optic axis. Nix and MacNair measured expansions perpendicular to the optic axis but presented only a coarse graph of the results, from which the following values of $10^6(dL/LdT)$ were taken: 7 at 100° K, 10 at 150°, 12 at 200°, 13 at 250°, 14 at 300° K.

^e Ebert [1928] has given two isolated data for ruby *mica* measured in the lamination plane. These are as follows: $10^5(L_{273}-L_{83})/L_{273}=120$ and $10^5(L_{273}-L_{20})/L_{273}=135$.

^f Extrapolated using Gruneisen correlation as explained in Introduction.

TABLE 2.4. Linear thermal contractions

Plastics and elastomers ^a

<i>T</i> <i>deg K</i>	$10^5(L_{233}-L_T)/L_{233}$									
	Araldite ^b 501	Catalin ^c	Dynakon ^d rod F	Dynakon ^e sheet A3A	Fluorothene ^f or Kel-F	Laminac ^g 4129	Lucite ^h	Nylon ⁱ	Panelyte ^j 942	Panelyte ^k 942
0	1061	849	282	428	1135	1202	1134	1389	364	836
20	1051	835	279	422	1114	1188	1123	1379	362	824
40	1022	811	271	407	1070	1154	1092	1352	355	801
60	983	779	261	388	1019	1104	1048	1308	344	770
80	935	740	248	366	962	1042	995	1247	329	733
100	880	695	233	342	900	971	936	1172	310	689
120	819	644	215	315	834	893	869	1088	288	639
140	751	588	194	286	763	811	796	996	263	584
160	676	528	172	255	686	724	717	896	236	524
180	594	464	148	222	604	632	632	789	207	459
200	505	397	123	187	517	535	540	673	176	389
220	410	325	98	150	424	432	441	548	143	314
240	308	247	72	111	324	323	335	412	108	235
260	199	161	45	70	214	207	220	265	70	151
273	122	100	27	42	134	126	136	161	43	93
280	81	67	18	28	90	84	91	107	29	62
293	0	0	0	0	0	0	0	0	0	0
300	-46	-40	-9	-15	-52	-47	-53	-61	-15	-32

^a Data from Laquer and Head [1952].^b Epoxy casting resin made by Ciba Co. 40 g of the material was catalyzed with 2 ml triethanolamine. Cured 8 hr at 120 °C and then 24 hr at 180 °C.^c Phenolic plastic made by Catalin Corp. of Am. 3/8 in. diameter rod.^d Glass fiber reinforced, molded polyester rod, 0.146 in. diameter, made by Dynakon Corp., Cleveland, Ohio.^e Same except 1/8 in. thick sheet.^f Polychlorotrifluoroethylene. The samples were, respectively, from a 5 in. diameter rod of Fluorothene made by Union Carbon and Carbide and from a 1/8 in. thick sheet of Kel-F made by M. W. Kellogg and Co.^g An unsaturated polyester made by American Cyanamide Co. Catalyzed

with 0.5 wt. % of tert. butyl hydroperoxide. Cured 48 hr at room temperature followed by 1 hr at 100 °C.

^h Polymethylmethacrylate. "Probably Du Pont Lucite". Average of two samples from rod stock.ⁱ From 3/4 in. diameter rod. "Probably E. I. Du Pont de Nemours and Co., grade FM-1".^j From a 1 in. diameter rod, grade 942. This is a molded, cloth-base, laminated phenolic made by Panelyte Div., St. Regis Paper Co. Measured parallel to the lamination and normal to the rod axis.^k Same except measured normal to both the lamination and the rod axis.Plastics and elastomers ^a

<i>T</i> <i>deg K</i>	$10^5(L_{233}-L_T)/L_{233}$									
	Plexiglas ^b	Polystyrene ^c	Polythene ^d	Rubber, ^e hard	Rubber, ^f Silastic 160	Selectron ^g 5026	Teflon ^h	Tenite I ⁱ	Tenite II ^j	Vinylite ^k
0	1220	1550	2449	1272	2301	1319	2140	1850	2304	1303
20	1210	1522	2439	1263	2296	1305	2110	1830	2284	1288
40	1160	1466	2404	1240	2276	1270	2060	1785	2244	1249
60	1110	1394	2349	1213	2231	1217	2000	1730	2189	1193
80	1050	1308	2279	1174	2161	1150	1930	1670	2114	1125
100	990	1211	2194	1128	2066	1075	1850	1600	2019	1050
120	930	1105	2089	1069	1951	994	1760	1520	1904	969
140	860	992	1964	1001	1816	907	1660	1425	1764	882
160	780	874	1814	942	1656	815	1540	1315	1604	789
180	690	752	1639	834	1466	718	1400	1190	1424	691
200	590	626	1439	736	1246	615	1240	1045	1219	587
220	490	499	1199	625	996	505	1050	880	994	475
240	370	368	919	501	721	386	855	690	749	354
260	240	232	594	364	441	256	645	465	484	225
273	150	141	359	256	256	164	500	290	299	136
280	99	93	239	181	165	112		195	199	90
293	0	0	0	0	0	0		0	0	0
298							0			
300	-55	-51	-131	-117	-119	-69		-115	-111	-50

^a Data from Laquer and Head [1952] except as otherwise noted. (In addition to the substances listed in the table, data have been given for 16 specially compounded rubbers by Dunsmoor et al. [1958] and Trepus et al. [1959]. These data consist mainly of values of $(L_{233}-L_T)/L_{233}$. See also Wood, Bekkedahl, and Peters [1939].)^b Polymethylmethacrylate made by Rohm and Haas Co. Data from Giauque, Geballe, Lyon, and Fritz [1952].^c Average of two samples from rod stock, both "probably American Phenolic Corp. grade 912A".^d Polyethylene made by E. I. Du Pont de Nemours and Co. Molded under 2000 psi pressure at 150 °C for 10 min. Directional variations were negligible. See also Hunter and Oakes [1945]. Five filled polythenes were measured by Head and Laquer [1952].^e Measured normal to a 1 in. thick slab made by W. H. Salisbury and Co. Shore hardness was 90 on the A2 scale. See also Dorsey [1908].^f A silicone rubber, hardness 77, made by Dow Corning Corp. Molded under 200 psi at 120 °C for 10 min. Cured 15 hr at 150 °C, 7 hr at 200 °C, and 17 hr at 250 °C. A similar sample that was uncured had a hardness of 48 on the Shore A2 scale. It was too soft to measure closer than $\pm 25\%$. Within these limits it was the same as the harder sample.^g An unsaturated polyester made by Columbia Resins Div., Pittsburgh

Plate Glass Co. Catalyzed with 0.5 wt % tert. butyl hydroperoxide. Cured 48 hr at room temperature, then 1 hr at 100 °C.

^h Polytetrafluoroethylene. Extruded and annealed sample measured by Kirby [1956]. He found that strained samples could have expansions larger or smaller than those of annealed Teflon, the differences being as large as 20%.Laquer and Head [1952] measured two samples of Du Pont Teflon rod taken normal and parallel to the extrusion direction. The expansions parallel were roughly 15% larger than those normal, and the average is 10 to 15% larger than the above data by Kirby. The data of Laquer and Head were used only to guide the extrapolation of Kirby's values below 80 °K. Teflon has a first order transition at 20 °C. Therefore we use 25 °C as a reference temperature and tabulate $10^5(L_{233}-L_T)/L_{233}$ above.ⁱ Formula 0072-MS. A cellulose acetate made by Tennessee Eastman Corp. Molded under 5000 psi pressure at 150 °C for 20 min.^j Formula 205A-MS. Otherwise same as above.^k Average of two types with nearly identical expansions made by Bakelite Corp.: (1) VYDR. 95% vinyl chloride, 5% vinyl acetate. Stabilized with 5 wt % dibutyl tin maleate and molded under 6500 psi pressure at 150 °C for 5 min. (2) VMCH. 86% vinyl chloride, 13% vinyl acetate, 3% dicarboxylic acid. Stabilized with 5 wt % dibutyl tin maleate and molded under 5000 psi pressure at 130 °C for 30 min.

TABLE 3. *Miscellaneous substances*

3.1. Mostly alloys. Data from Gregg [1954]

Substance	Rockwell Hardness	$10^4(L_{294}-L_T)/L_{294}$		
		$T=194^\circ\text{K}$	$T=166^\circ\text{K}$	$T=77^\circ\text{K}$
High speed steel (18 W, 4 Cr, 1 V).....	C 63	11	14	20
High speed steel (6 W, 5 Mo, 4 Cr, 2 V).....	C 64	11	13	20
High speed steel (18 W, 4 Cr, 2 V, 9 Co).....	C 65	10	13	18
High speed steel (5 W, 4 Cr, 4 V, 4 Mo).....	C 64	13	16	23
High speed steel (4 W, 5 Mo, 4 Cr, 1 V, 12 Co).....	C 67	10	12	16
Tool steel (1.10 C).....	C 66	12	14	20
Tool steel (0.90 C, 1.20 Mn, 0.50 Cr, 0.50 W).....	C 63	12	14	20
Tool steel (0.50 C, 0.90 Cr, 1.25 W).....	C 66	12	15	18
Tool steel (2.25 C, 12.00 Cr, 1.00 Mo).....	C 64	13	14	20
Chrome vanadium steel (SAE 6150).....	C 58	13	15	22
Aluminum (25).....	H 64	22	28	31
Cast alloy (20 Co, 8 W, 7 Mo, 5 Cr, 2 V, 0.7 C, .7 B, bal. Fe).....	C 69	9	11	15
Cast alloy (44 Co, 17 W, 33 Cr, 2.25 C, 2 Fe).....	C 58	10	13	18
Carboloy (Grade 44 A).....	A 91	2	3	8
Bronze ^a (SAE 660).....	F 78	19	22	33
Cast iron ^b	B 85	11	13	19

^a See also Henning [1907].^b See also Beenakker and Swenson [1955], Chevenard [1926].

3.2. Various alloys. Data from Lucks and Deem [1958]

Substance ^d	Condition	$10^5(L_{293}-L_T)/L_{293}$		
		$T=200^\circ\text{K}$	$T=144^\circ\text{K}$	$T=116^\circ\text{K}$
Aluminum, 2024 ^a (4.5 Cu, 1.5 Mg, 0.6 Mn).....	T 4 ^e	194	294	345
Aluminum, 7075 ^a (5.5 Zn, 2.5 Mg, 1.5 Cu, 0.3 Cr, 0.2 Mn).....	T 6 ^e	185	276	314
Inconel-X (73 Ni, 15 Cr, 7 Fe, 2.5 Ti, 1 Cb, 0.7 Al, 0.4 Si, 0.5 Mn).....	Hot rolled. Solution treated 3 hr at 2100 °F, air cooled. Double aged 24 hr at 1550 °F, air cooled; 20 hr at 1300 °F, air cooled.	113	176	206
Magnesium, A-N-M-29 (3 Al, 1 Zn, 0.3 Mn).....	Hot rolled. Annealed 1 hr at 600 °F. Furnace cooled.....	^b 231	^b 353	^b 408
"K" Monel ^c (66 Ni, 29 Cu, 2.75 Al, 0.9 Fe, 0.75 Mn, 0.5 Si, 0.15 C, 0.005 S).....	Hot rolled. Annealed 1 hr at 1650 °F. Water quenched.....	115	176	206
Steel, SAE 1010 (0.10 C, 0.5 Mn).....	Hot rolled.....	98	148	172

^a See also Fontana [1948, 1953].^b Average of three mutually perpendicular orientations. Values in the rolling direction were 2% lower; values in the rolling plane but transverse to the rolling direction were 5% lower; values normal to the rolling plane were 7% higher.^c K-Monel has a Curie point at about 160 °K. The above data are too sparse to indicate if there is an appreciable anomaly in the expansion at the Curie point.^d The compositions given are nominal or average ones for these alloys. They were taken from the ASM Metals Handbook, 1948 edition, in which alloy 2024 is listed as alloy 24S, alloy 7075 is listed as alloy 75S and magnesium A-N-M-29 is listed as alloy AZ31X.^e Solution treatment and precipitation. See ASM Metals Handbook for details.3.3. Optical glasses. Data from Molby [1949] ^o

T	$10^5 \frac{L_{293}-L_T}{L_{293}}$													
	Crown C-1 ^a	Borosilicate crown BSC-1 ^a	Borosilicate crown BSC-2 ^a	Light barium crown LBC-2 ^a	Dense barium crown DBC-1 ^a	Dense barium crown DBC-3 ^a	Dense flint DF2 ^a	Extra dense flint EDF-3 ^a	Barium flint BF-1 ^a	Crown flint CF-1 ^a	Glass #11 ^b	Glass #32 ^b	Glass #33 ^b	Glass #45 ^b
deg K														
80	134	133	112	137	110	105	136	139	142	110	100	102	92	96
90	130	128	109	132	107	101	131	135	137	107	97	99	90	94
100	126	124	105	128	104	98	126	130	133	104	94	96	87	91
120	116	114	97	117	95	90	115	118	122	95	88	89	83	85
140	106	104	88	106	87	82	104	106	111	87	80	81	74	78
160	95	92	77	95	77	73	92	94	98	77	72	72	66	70
180	82	80	66	82	67	63	79	81	85	67	63	63	58	62
200	69	67	57	68	56	53	66	67	71	56	53	53	49	52
220	55	53	45	54	44	42	52	53	56	44	42	42	39	42
240	41	39	33	40	33	31	38	39	41	33	31	31	29	31
260	26	25	21	25	21	20	24	25	26	21	20	20	18	20
273	16	15	13	15	13	12	15	15	16	13	12	12	11	12
280	10	10	8	10	8	8	9	10	10	8	8	8	7	8
293	0	0	0	0	0	0	0	0	0	0	0	0	0	0
300	-6	-6	-5	-5	-5	-4	-5	-5	-5	-5	-4	-4	-4	-4

^a Bausch and Lomb Co. designation. Composition was not given.^b Eastman Kodak Co. designation. Composition was not given.^o Dorsey [1907] also gives data on a crown glass. Composition not stated.

TABLE 4. Anisotropy of single crystals

4.1.^a Antimony, beryllium, bismuth, tin (white)

T_2	T_1	$\frac{10^6}{L_{293}} \frac{L_2 - L_1}{T_2 - T_1}$							
		Antimony		Beryllium		Bismuth		Tin (white)	
			⊥		⊥		⊥		⊥
<i>deg K</i>	<i>deg K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>
293	273	16.18	8.24	8.59	11.70	16.20	11.60	28.99	15.83
273	233	16.17	8.11	7.58	10.73	16.20	11.53	27.98	15.60
233	193	16.15	7.84	5.81	8.65	16.20	11.38	26.67	15.00
193	153	16.11	7.43	3.97	6.09	16.08	11.04	25.09	14.22
153	113	16.09	6.78	2.07	3.45	15.94	10.59	24.44	13.08
113	90	15.81	6.04	0.73	1.58	15.86	9.89	23.23	11.79
90	78	15.48	5.27	-----	0.79	15.55	9.25	22.45	10.66
90	57	-----	-----	0.13	-----	-----	-----	-----	-----
78	58	14.7	4.2	-----	-----	14.9	8.5	20.57	8.58
58	20	-----	-----	-----	-----	13.3	5.1	-----	-----

^a The tabulated values are average expansion coefficients in the intervals, T_1 to T_2 , measured parallel and normal, respectively, to the trigonal (anti-

mony, bismuth), hexagonal (beryllium), or tetragonal (tin) axis. The data are from Erling [1939].

4.2.^a Cadmium, zinc

T_2	T_1	$\frac{10^6}{L_{293}} \frac{L_2 - L_1}{T_2 - T_1}$			
		Cadmium		Zinc	
			⊥		⊥
<i>deg K</i>	<i>deg K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>
293	253	54.3	19.1	64.3	+12.5
253	213	55.4	17.8	65.1	11.3
213	173	56.7	16.4	65.4	10.1
173	133	58.0	14.6	65.6	8.3
133	93	58.9	11.7	64.4	+5.0
86	20	54.5	3.6	52.5	-2.1

^a The tabulated values are average expansion coefficients in the intervals, T_1 to T_2 , measured parallel and normal, respectively, to the hexagonal axis. The data are from Gruneisen and Goens [1924].

4.3.^a Magnesium

T_2	T_1	$\frac{10^6}{L_{293}} \frac{L_2 - L_1}{T_2 - T_1}$	
			⊥
		<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>
<i>deg K</i>	<i>deg K</i>		
293	193	25.7	24.3
193	90	20.3	18.8
90	78	13.8	13.0
78	20	5.8 _s	5.3 _s

^a The tabulated values are average expansion coefficients in the intervals, T_1 to T_2 , measured parallel and normal, respectively, to the hexagonal axis. The data are from Goens and Sehmud [1936].

4.4. Mercurey

T	$10^6 \times \text{Expansion coefficient}^a$		Source
		⊥	
	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	
<i>deg K</i>	<i>deg⁻¹ K</i>	<i>deg⁻¹ K</i>	
158	49.8	37.7	Hill [1935]
113	44.9	35.2	Hill [1935]
83 to 113	42.6	33.4	Hill [1935]
85 to 194	47.0	37.5	Gruneisen and Sekell [1934]

^a The first two lines give instantaneous expansion coefficients, $10^6(dL/LdT)$, while the last two lines give average expansion coefficients, $(10^6/L)[(L_2 - L_1)/(T_2 - T_1)]$, in the indicated temperature intervals. The directions of measurement were parallel and normal, respectively, to the trigonal axis.

References¹

- Ackerman, D. E., Properties of Monel at low temperatures, *Metal Progr.* **30**, No. 5, 56-60 (1936). [105 to 300 °K.]
- Adenstedt, H., Thermal expansion of solids at low temperatures (Cu, Ni, Fe, zincblende, LiF, calcite, aragonite, NH₄Cl), *Ann. Physik* **26**, 69-96 (1936). [20 to 273 °K. In German.]
- *van Agh, F. P. G., and H. K. Onnes, On the measurement of very low temperatures. XXXII. The thermal expansion of Jena glass 16 III, *Leiden Comm. No. 176a* (1925). [20 to 371 °K.]
- Altman, H. W., T. Rubin, and H. L. Johnston, Coefficients of thermal expansion of solids at low temperatures. II. The thermal expansion of Monel, Inconel, Contracid, SAE 1020 low carbon steel and type 410 stainless steel. Report TR 264-19 (1952). Cryogenic Laboratory, The Ohio State University. ASTIA Document ATI 158988. [20 to 300 °K.]
- Altman, H. W., T. Rubin, and H. L. Johnston, Coefficient of thermal expansion of solids at low temperatures. III. The thermal expansion of pure metals, with the data for aluminum, nickel, titanium and zirconium, Ohio State U. Tech. Report 264-27 (1954). ASTIA Document AD 26970. [15 to 300 °K.]
- Altman, H. W., T. Rubin, and H. L. Johnston, Coefficient of thermal expansion of solids at low temperatures. IV. The thermal expansion of type 304 stainless steel and yellow brass. Report TR 264-28 (1954). Cryogenic Laboratory, The Ohio State University. ASTIA Document AD 31268. [14 to 300 °K.]
- Aoyama, S., and T. Ito, Thermal expansion of nickel-copper alloys at low temperatures (Part I), *Sci. Repts. Tohoku Univ.* **27**, 348-364 (1939). [Ni, Cu, 13 Ni-Cu alloys. 77 to 273 °K. In English.]
- *Armstrong, P. E., O. N. Carlson, and J. F. Smith, Elastic constants of thorium single crystals in the range 77-400 °K, *J. Appl. Phys.* **30**, 36-41 (1959). [Includes thermal expansion, 80 to 400 °K.]
- Austin, J. B., H. Saini, J. Weigle, and R. H. H. Pierce, A direct comparison on a crystal of calcite of the X-ray and optical interferometer methods of determining linear thermal expansion. *Phys. Rev.* **57**, 931 (1940). [Room temperature.]
- Ayres, H. D., Coefficients of linear expansion at low temperatures, *Phys. Rev.* **20**, 38-51 (1905). [Al, Ag. 86 to 372 °K.]

¹ References are arranged alphabetically by authors. The prefix (*) indicates selected references not referred to in the text or tables. The prefix (T) indicates references devoted primarily to experimental techniques. Titles in foreign languages have been freely translated in order to indicate content and have been supplemented where necessary by additional indications of content placed in brackets.

- *Banister, J. R., S. Legvold, and F. H. Spedding, Structure of Gd, Dy, Er at low temperatures, *Phys. Rev.* **94**, 1140-2 (1954). [NaCl, Gd, Dy, Er. 42 to 300 °K.]
- *Barrett, C. S., Crystal structure of barium and europium at 293, 78, and 5°K, *J. Chem. Phys.* **25**, 1123 (1956).
- Barrett, C. S., X-ray study of the alkali metals at low temperature, *Acta Cryst.* **9**, 671-7 (1956). [Na, Li, K, Rb, Cs. 5 to 78 °K.]
- Barron, T. H. K., On the thermal expansion of solids at low temperatures, *Phil. Mag.* **46**, 720-734 (1955). [Theoret.]
- Barron, T. H. K., Low temperature deviations from Gruneisen's theory of the thermal expansion of solids. *Conf. Phys. Basses Temps.*, Paris (1955), Annexe 1955-3, Suppl. Bull. inst. intern. froid, pp. 448-452. [Theoret. In English.]
- *Barron, T. H. K., Gruneisen parameters for the equation of state of solids, *Ann. Phys.* **1**, 77-90 (1957). [Theoret.]
- *Barson, F., S. Legvold, and F. H. Spedding, A low temperature dilatometric study of some rare-earth metals, AEC Publ. No. ISC-424 (1953). *Tech. Inform. Serv.*, Oak Ridge, Tenn. [La, Pr, Nd, Gd, Dy, Er. 100 to 350 °K.]
- *Barson, F., S. Legvold, and F. H. Spedding, Thermal expansion of rare earth metals, *Phys. Rev.* **105**, 418-424 (1957). [Gd, Tb, Dy: 120 °K and up. La, Ce, Pr, Nd, Er, Yb: 300 °K and up.]
- Baskin, Y., and L. Meyer, Lattice constants of graphite at low temperatures, *Phys. Rev.* **100**, 544 (1955). [4 to 297 °K.]
- Beattie, J. A., B. E. Blaisdell, J. Kaye, H. T. Gerry, and C. A. Johnson, An experimental study of absolute temperature scale. VIII. The thermal expansion and compressibility of vitreous silica and the thermal dilatation of mercury, *Proc. Am. Acad. Arts Sci.*, **74**, 371 (1941). [Silica glass. -200 to +450 °C.]
- Beenakker, J. J. M., and C. A. Swenson, Total thermal contractions of some technical metals to 4.2 °K, *Rev. Sci. Instr.* **26**, 1204-5 (1955). [Brass, german silver, Cu, beryllium-copper, stainless steels 302-304-316, 70 Cu-30 Ni, cast iron, cold-rolled steel, 1020 steel, Invar.]
- *Bekkedahl, N., Forms of rubber as indicated by temperature-volume relationship, *J. Research NBS* **13**, 411-431 (1934). [Natural rubber hydrocarbon. 83 to 330 °K.]
- Berry, C. R., Effect of internal strains on linear expansion, x-ray lattice constant, and density of crystals, *J. Appl. Phys.* **24**, 658 (1953). [Review.]
- *Bijl, D., The thermal expansion of some simple solids at low temperatures. *Conf. Phys. Basses Temps.*, Paris (1955), Annexe 1955-3, Suppl. Bull. inst. intern. froid, pp. 445-7. [Variation of the Gruneisen constant with temperature for Ag, Al, Cu, Fe, KBr. In English.]
- Bijl, D., The representation of specific heat and thermal expansion data of simple solids, *Progress in Low Temperature Physics*, Vol. II (1957), pp. 395-430. [Review.]
- Bijl, D., and H. Pullan, Thermal expansion of simple solids at low temperatures and Gruneisen's law, *Phil. Mag.* **45**, 290-4 (1954). [Cu, Al, Fe. Theoret.]
- Bijl, D., and H. Pullan, A new method for measuring the thermal expansion of solids at low temperatures; The thermal expansion of copper and aluminum and the Gruneisen rule, *Physica* **21**, 285-298 (1955). [Cu, Al. 20 to 273 °K.]
- *Biltz, W., W. Fischer, and E. Wunnenberg, Molecular and atomic volumes. 25. Volumes of organic crystals at low temperatures, *Z. physik. Chem.* **151**, 13-55 (1930). [Two score organic substances. 78° and up. In German.]
- *Biltz, W., and A. Sapper, Molecular and atomic volumes. 34. Low temperature densities of some halides of elements of the fourth through the sixth group, *Z. anorg. u. allgem. Chem.* **203**, 277-306 (1932). [78 and 194 °K. In German.]
- Bishop, S. M., J. W. Spretnak, and M. G. Fontana, Mechanical properties, including fatigue of titanium-base alloys RC-130-B and Ti-150-A at very low temperatures, *Trans. Am. Soc. Metals* **45**, 993-1007 (1953). [77 to 293 °K.]
- *Black, I. A., L. H. Bolz, F. P. Brooks, F. A. Mauer, and H. S. Peiser, A liquid-helium cold cell for use with an x-ray diffractometer, *J. Research NBS* **61**, 367-371 (1958).
- *Blackman, M., On the thermal expansion of solids, *Proc. Phys. Soc.* **B70**, 827 (1957). [Theoret.]
- *Blackman, M., On negative volume expansion coefficients, *Phil. Mag.* **3**, 831-8 (1958). [Theoret.]
- Boas, W., and R. W. K. Honeycombe, The anisotropy of thermal expansion as a cause of deformation in metals and alloys, *Proc. Roy. Soc. A* **188**, 427 (1947). [Sn, Cd, Zn, and alloys. 83 °K and up.]
- Borelius, G., and C. H. Johansson, Expansion measurements at low temperatures with double mirror dilatometer, *Ann. Physik* **75**, 23-36 (1924). [Cu, Zn, Cd. 103 to 273 °K. In German.]
- Buffington, R. M., and W. M. Latimer, The measurement of coefficients of expansion at low temperatures; Some thermodynamic applications of expansion data, *J. Am. Chem. Soc.* **48**, 2305-19 (1926). [Al, Ag, Cu, Pyrex, NaCl, quartz. 85 to 300 °K.]
- *Calhoun, B. A., and S. C. Abrahams, A low temperature adaptor for the Norelco High Angle Spectrometer, *Rev. Sci. Instr.* **24**, 397 (1953). [78 °K and up.]
- Carpenter, L. G., and F. H. Oakley, Thermal expansion and atomic heat of solid mercury, *Phil. Mag.* **12**, 511 (1931). [183 to 231 °K.]
- *Cheesman, G. H., and C. M. Soane, The lattice constants of the inert elements, *Proc. Phys. Soc.* **B70**, 700-2 (1957). [Xe, Kr. 58 to 89 °K.]
- Chevenard, P., Nickel steels, *Rev. mét.* **11**, 841-862 (1914). [Fe-Ni alloys. 20 °K and up. In French.]
- Chevenard, P., Thermal anomalies of certain solid solutions, *J. Inst. Metals* **36**, 39-62 (1926). [Cast iron, Ni, Ni-Cr alloys. 120 °K and up.]
- *Childs, B. G., The preparation of metal single crystals for expansion measurements, *J. Sci. Instr.* **27**, 102 (1950).
- *Childs, B. G., The thermal expansion of anisotropic metals, *Revs. Modern Phys.* **25**, 665-70 (1953). [Review.]
- Cohen, E., and J. Olie, Atomic volumes of allotropic modifications at very low temperatures. I., *Z. physik. Chem.* **71**, 385-400 (1910) or *Leiden Comm.* No. 113. [Diamond, graphite, white tin, gray tin. 110 to 291 °K. Latter ref. in English.]
- Connell, L. F., and H. C. Martin, Concerning reported discrepancies between x-ray and macroscopic measurements of thermal expansion of some alkali halides, *Acta Cryst.* **4**, 75-6 (1951). [Kl, KBr. 293 to 473 °K.]
- Corliss, L. M., J. M. Hastings, and R. J. Weiss, Antiphase antiferromagnetic structure of chromium, *Phys. Rev. Letters* **3**, 211-2 (1959).
- Corruccini, R. J., and J. J. Gniewek, Specific heats and enthalpies of technical solids at low temperatures: a compilation from the literature. *NBS Mono.* 21 (1960).
- *Cruikshank, D. W. J., E. Mendoza, and J. H. Robertson, Summarized proceedings of a conference on low temperature crystallography—Oxford, April 1956. *Brit. J. Appl. Phys.* **7**, 425 (1956). [Includes unpubl. data by Dobbs on Kr at 75 to 105 °K.]
- *Davies, R. O., and G. O. Jones, Thermodynamic and kinetic properties of glasses, *Advances in Phys.* **2**, 370 (1953). [Review. Illustrates the effect of glass transitions on dilatation.]
- *Dayal, B., The theory of the thermal expansion of diamond, *Proc. Indian Acad. Sci.* **A20**, 187-191 (1944).
- *Dayal, B., The thermal expansion of metals at low temperatures, *Proc. Indian Acad. Sci.* **A20**, 192-9 (1944). [Theoret.]
- *Dayal, B., Theory of the thermal expansion of the alkali halides, *Proc. Indian Acad. Sci.* **A20**, 145-154 (1944). [NaCl, KCl, KBr.]
- Dennison, D. M., The crystal structure of ice, *Phys. Rev.* **17**, 20 (1921). [83 °K.]
- Dewar, J., Coefficients of the cubical expansion of ice, hydrated salts, solid carbonic acid and other substances at low temperatures, *Proc. Roy. Soc.* **70**, 237-246 (1902). [27 miscellaneous substances. 84 to 289 °K.]

- Dheer, P. N., and S. L. Surange, Thermal expansion of lead at low temperatures, *Phil. Mag.* **3**, 665-74 (1958). [4.5 to 10 °K.]
- Disch, J., Thermal expansion of several substances. II, *Z. Physik* **5**, 173-5 (1921). [Cr, Mn, Mo, Ni, Ta, W. 83 to 773 °K. In German.]
- *Dobbs, E. R., and G. O. Jones, Theory and properties of solid argon, *Repts. Progr. in Phys.* **20**, 516-564 (1957). [20 to 80 °K.]
- *Dobbs, E. R., and K. Luszczynski, The lattice constant of solid krypton. *Conf. Phys. Basses Temps.*, Paris (1955), Annexe 1955-3, Suppl. Bull. inst. intern. froid, pp. 439-440. [91° K. In English.]
- *Domb, C., and J. S. Dugdale, Solid helium, *Progress in Low Temperature Physics*, Vol. II, Interscience Publ. 1957, pp. 338-367. [Review.]
- Dorsey, H. G., Coefficient of linear expansion at low temperatures, *Phys. Rev.* **25**, 88-102 (1907). [Cd, Ag, Sn, Cu, Au, Bi, Sb, Pt, crown glass, Fe, soft solder, silica glass. 93 to 293 °K.]
- Dorsey, H. G., Further measurements of the coefficient of linear expansion at low temperatures, *Phys. Rev.* **27**, 1-10 (1908). [Au, Pb, Se, Zn, quartz, hard rubber, hard fiberboard. 93 to 293 °K.]
- Dorsey, H. G., Coefficients of linear expansion at low temperatures, *Phys. Rev.* **30**, 271-2 (1910). [Abstract. 8 carbon steels, fused silica. 93 to 293 °K.]
- *Druyvesteyn, M. J., Some remarks on the thermal expansion and the Poisson contraction of the cubic metals, *Philips Research Repts.* **1**, 77-80 (1946). [Review.]
- *Dugdale, J. S., and D. K. C. MacDonald, The thermal expansion of solids, *Phys. Rev.* **89**, 832-4 (1953). [Theoret.]
- van Duijn, J., and J. van Galen, Influence of vacancies on the thermal expansion of lead near the melting point, *Physica* **23**, 622 (1957).
- Dunsmoor, R. J., F. W. Tipton, G. E. Trepus, J. J. Hill, and H. A. Mahle, Design criteria for "O"-rings and similar elastic seals, Boeing Airplane Co., Document No. D2-2964, July, 1958. [Rubbers. 78 to 293 °K.]
- Durand, M. A., The coefficient of thermal expansion of magnesium oxide, *Physics* **7**, 297-8 (1936). [85 to 480 °K.]
- Ebert, H., Expansion measurements at low temperatures *Z. Physik* **47**, 712-722 (1928). [Al, Ag, Au, Fe, Mg, Pb, Jena glasses 16 III and 59 III, 3 Berlin porcelains, mica. 20 to 373 °K. In German.]
- [†]Ebert, H., Measurement of thermal expansion. Review of methods for solids, *Arch. tech. Messen*, Issue 158 (V9211-1), pp. 121-3, Dec. 1948. [In German.]
- [†]Eeles, E. G., A precision low temperature X-ray camera, *Advances in Cryogenic Eng.* **3**, 248-53, (1957). Plenum Press. [Liquid He region.]
- *Ellefson, B. S., and N. W. Taylor, Crystal structures and expansion anomalies of MnO, MnS, FeO, Fe₃O₄ between 100 °K and 200 °K, *J. Chem. Phys.* **2**, 58-64 (1934).
- Erfiling, H. D., Thermal expansion of solids at low temperatures. II. (Cr, β -Mn, Mo, Rh, Be, graphite, Ti, Zr, Bi, Sb, Sn, and beryl), *Ann. Physik* **34**, 136-60 (1939). [57 to 293 °K. In German.]
- Erfiling, H. D., Change in thermal expansion and electrical resistance of γ -manganese upon transformation to α -phase, *Ann. Physik* **37**, 162-8 (1940). [78 to 293 °K. In German.]
- Erfiling, H. D., Thermal expansion of solids at low temperatures. III. (Ca, Nb, Th, V, Si, Ti, Zr), *Ann. Physik* **41**, 467-475 (1942). [57 to 300 °K. In German.]
- Eshelby, J. D., Geometrical and apparent x-ray expansions of a crystal containing lattice defects, *J. Appl. Phys.* **24**, 1249 (1953). [Letter. Theoret.]
- Eshelby, J. D., Distortion of a crystal by point imperfections, *J. Appl. Phys.* **25**, 255 (1954). [Theoret.]
- Eshelby, J. D., The continuum theory of lattice defects, *Solid State Physics* **3**, 79-144 (1956). [Theoret.]
- Feder, R., and A. S. Nowick, Use of thermal expansion measurements to detect lattice vacancies near the melting point of pure lead and aluminum, *Phys. Rev.* **109**, 1959-1963 (1958).
- Fiedler, H. C., B. L. Averbach, and M. Cohen, The effect of deformation on the martensitic transformation in austenitic stainless steels, *Trans. ASM* **47**, 269 (1955).
- Figgins, B. F., G. O. Jones, and D. P. Riley, The thermal expansion of aluminium at low temperatures as measured by an x-ray diffraction method, *Phil. Mag.* **1**, 747-758 (1956). [20 to 299 °K.]
- *Figgins, B. F., and B. L. Smith, Density and expansivity of solid krypton, *Phil. Mag.* **5**, 186-8 (1960). [20 to 90 °K.]
- Fine, M. E., Elasticity and thermal expansion of germanium between -195 and 275 °C, *J. Appl. Phys.* **24**, 338-340 (1953). [100 to 550 °K.]
- Fine, M. E., C_p - C_v in silicon and germanium, *J. Chem. Phys.* **21**, 1427 (1953). [Letter. Si. 95 to 425 °K.]
- Fine, M. E., E. S. Greiner, and W. C. Ellis, Transitions in chromium, *Trans. A.I.M.E. (J. Metals)*, **189**, 56-8 (1951). [78 to 673 °K.]
- *Foex, M., A transformation common to the monoxides of manganese, iron, cobalt and nickel, *Compt. rend.* **227**, 193-4 (1948). [MnO, FeO, CoO, NiO. 78 to 673 °K. Illustrates anomaly at Neel point. In French]
- Fontana, M. G., Investigation of mechanical properties and physical metallurgy of aircraft alloys at very low temperatures. Part II. Strength properties and hardness, *Air Force Tech. Report No. 5662 Part II.* (1948). [Aluminums 28, 24S, 61S, 75S, and 125S, magnesium FS-1, aluminum bronze, SAE 2330 and 8630 steels, stainless steels 304 and 322, 8½% nickel steel. 80 to 300 °K.]
- Fontana, M. G., S. M. Bishop, and J. W. Spretnak, Mechanical properties of metals at low temperatures, *Air Force Tech. Report No. 5662-V* (1953). [Aluminum alloys 24S-T4 and 75S-T6, SAE 8630 steel, Ti, type 304 stainless steel. 20 to 290 °K.]
- Fraser, D. B., and A. C. Hollis-Hallett, Total contractions of some metals on cooling from room temperature to 4° K, *Proc. 9th Intern. Congr. Refrig.* (1955). Vol. 1, pp. 1064-6. [Brass, Cu, Duralumin, Monel, "stainless steel".]
- Furman, D. E., Thermal expansion characteristics of stainless steels between -300° and 1000°F, *Trans. A.I.M.E. (J. Metals)* **188**, 688-691 (1950). [Types 301, 304, 316, 347, 310, 330 stainless steel. 90 to 810 °K.]
- Giauque, W. F., T. H. Geballe, D. N. Lyon, and J. J. Fritz, Some properties of plastics and the use of plastic apparatus at low temperatures, *Rev. Sci. Instr.* **23**, 169-173 (1952). [Plexiglas. 20 to 300 °K.]
- Gibbons, D. F., Thermal expansion of some crystals with the diamond structure, *Phys. Rev.* **112**, 136-40 (1958). [Si, Ge, InSb. 4 to 300 °K.]
- Glover, R. E., Lattice expansion of KCl single crystals between 20 °C and 600 °C, *Z. Physik* **138**, 222-236 (1954). [In German.]
- Goens, E., and E. Schmid, Elastic constants, resistivity and thermal expansion of magnesium crystal, *Phys. Z.* **37**, 385-391 (1936). [21 to 473 °K. In German.]
- Gott, A., Thermal lattice expansion and macroscopic expansion of alkali halides crystallized from the melt, *Ann. Physik* **41**, 520 (1942). [290 °K and up. In German.]
- Graham, J., A. Moore, and G. V. Raynor, The effect of temperature on the lattice spacings of indium, *J. Inst. Metals* **84**, 86-7 (1955). [90 to 408 °K.]
- Gregg, H. T., Sub-zero treatment of metals, *G. E. Review*, July 1954, pp. 19-21. [23 miscellaneous materials. 77 to 294 °K.]
- Gruneisen, E., Thermal expansion of metals, *Ann. Physik* **33**, 33-64 (1910). [Ir, Mg, Zn, Cd, Sb, Au, Pb, Bi, Sn. 90 to 290 °K. In German.]
- Gruneisen, E., *Geiger-Scheel Handbuch der Physik* (1926). Vol. X. Thermal properties of matter, Chapt. 1 The solid state, Sec. d. Change of state of solids. [Review. In German.]
- Gruneisen, E., and E. Goens, Investigations on metallic crystals III. Thermal expansion of zinc and cadmium, *Z. Physik* **29**, 141-156 (1924). [Zn, Cd, Jena glass. 20 to 373 °K. In German.]
- Gruneisen, E., and O. Sckell, Mercury crystals: density, resistivity, thermal expansion, elastic constants, *Ann. Physik* **19**, 387-408 (1934). [83 to 195 °K. In German.]

- ^THaynes, F. G., Automatic recording of dilatometer measurements, *Bull. Inst. Metals* **2**, 193-6 (1954). (Accompanies *J. Inst. Metals*, Vol. 83).
- Head, E. L., and H. L. Laquer, Low temperature thermal expansion of various materials, AEC-D-3706 (1952), Office of Technical Services, Dept. Commerce, Washington 25, D.C. [B, Ti, Rh, Mg, Zn, Li, U, Pyrex, LiH, NaF, filled polythenes. Includes unpublished data on Pb by Altman, Rubin, and Johnston. 20 to 300 °K.] To be published.
- *Henglein, Fr. A., Thermal expansion of some alkali metal halides at low temperatures, *Z. physik. Chem.* **115**, 91-120 (1925). [NaCl, KCl, NaBr, KBr, NaI, KI. 89 to 300 °K. In German.]
- *Henglein, F. A., Thermal expansion of some alkali metal halides at low temperatures. II., *Z. physik. Chem.* **117**, 285-292 (1925). [LiF, LiCl, LiBr, LiI, NaF, KF, RbCl, RbBr, RbI. 89 to 273 °K. In German.]
- *Henglein, F. A., Thermal expansion in crystals and chemical constitution, *Z. Elektrochem.* **31**, 424-8 (1925). [A summary based on the data on 15 alkali halides from the preceding two references. In German.]
- Henning, F., The expansion of solids at low temperatures, *Ann. Physik* **22**, 631 (1907). [Jena glass 59 III, silica glass, porcelain, Pt, Pd, Pt-Ir, Ag, Cu, Ni, Al, constantan, bronze, brass, cast iron, ingot iron, wrought iron, soft steel. 82 to 289 °K. In German.]
- *Heuse, W., Molar volumes of hydrocarbons and some other substances at low temperature, *Z. physik. Chem.* **A147**, 266-274 (1930). [A score of hydrocarbons, NH₃, CO₂, acetone, Br₂, Cl₂, NO, N₂O, H₂O. 20 °K only. In German.]
- *Heuse, W., Dilatometric observation of the transformation point of methane, *Z. physik. Chem.* **A147**, 282-7 (1930). [20.1 to 20.8 °K. In German.]
- Hidnert, P., Thermal expansion of tantalum, *BS J. Research* **2**, 887-896 (1929). [83 to 773 °K.]
- Hidnert, P., Thermal expansion of artificial graphite and carbon, *J. Research NBS* **13**, 37-51 (1934). [293 to 1273 °K.]
- Hidnert, P., Thermal expansion of electrolytic chromium, *J. Research NBS* **26**, 81-91 (1941). [168 to 990 °K.]
- Hidnert, P., Thermal expansion of cast and of swaged chromium, *J. Research NBS* **27**, 113-124 (1941). [83 to 980 °K.]
- Hidnert, P., Thermal expansion of titanium, *J. Research NBS* **30**, 101-105 (1943). [83 to 973 °K.]
- Hidnert, P., and M. G. Blair, Thermal expansivity and density of indium, *J. Research NBS* **30**, 427-33 (1943). [83 to 373 °K.]
- Hidnert, P., and H. S. Krider, Thermal expansion of columbium, *BS J. Research* **11**, 279-284 (1933). [138 to 578 °K.]
- ^THidnert, P., and W. Souder, Thermal expansion of solids, *NBS Circular* 486 (1950).
- Hidnert, P., and W. T. Sweeney, Thermal expansion of tungsten, *BS Sci. Pap.* **20**, 483-7 (1925). [173 to 773 °K.]
- Hidnert, P., and W. T. Sweeney, Thermal expansion of beryllium and aluminum-beryllium alloys, *BS Sci. Pap.* **22**, 533-545 (1927). [153 to 973 °K.]
- Hidnert, P., and W. T. Sweeney, Thermal expansion of magnesium and some of its alloys, *BS J. Research* **1**, 771-792 (1928). [90 to 773 °K.]
- Hill, D. M., The principal expansion coefficients of single crystals of mercury, *Phys. Rev.* **48**, 620-4 (1935). [83 to 158 °K.]
- Hordon, M. J., B. S. Lement, and B. L. Averbach, Influence of plastic deformation on expansivity and elastic modulus of aluminum, *Acta Met.* **6**, 446-453 (1958). [77 to 300 °K.]
- Hull, D., and H. M. Rosenberg, Microscopy at liquid helium temperatures: phase transition in sodium, *Phys. Rev. Letters* **2**, 205-6 (1959).
- Hume-Rothery, W., On Gruneisen's equation for thermal expansion, *Proc. Roy. Soc.* **57**, 209-222 (1945). [Theoret.]
- Hume-Rothery, W., and K. W. Andrews, The lattice spacing and thermal expansion of copper, *J. Inst. Metals* **68**, Part 2, 19-26 (1942) Paper No. 915. [291 to 1144 °K.]
- Hume-Rothery, W., and T. H. Boulton, The coefficients of expansion of some solid solutions in aluminium, *Phil. Mag.* **40**, 71 (1949). [223 to 473 °K.]
- *Hume-Rothery, W., and K. Lonsdale, The lattice spacing of rubidium between -183 °C and +19 °C, *Phil. Mag.* **36**, 842-5 (1945).
- ^THume-Rothery, W., and D. J. Strawbridge, A general purpose Debye-Scherrer camera and its application to work at low temperatures, *J. Sci. Instr.* **24**, 89-91 (1947). [Al. 175 °K and up.]
- Hunter, E., and W. G. Oakes, The effect of temperature on the density of Polythene, *Trans. Faraday Soc.* **41**, 49-56 (1945). [95 to 443 °K.]
- Jacobs, R. B., and A. Goetz, The thermal expansion of the Bi lattice between 25° and 530° Abs., *Phys. Rev.* **51**, 159-164 (1937).
- Jaffee, R. I., and R. H. Ramsey, Properties of aluminum bronzes at subzero and high temperatures, *Metal Progr.* **54**, 57 (1948). [172 °K and up.]
- Jakob, M., and S. Erk, Thermal expansion of ice between 0° and -253°, *Z. Kalteind.* **35**, 125-130 (1928). [20 to 273 °K. In German.]
- *Johansson, C. H., Thermal expansion of some binary solid-solution series, *Ann. Physik* **76**, 445-454 (1925). [Ag-Pd. Cu-Pd. 83 to 300 °K. In German.]
- *Justi, E., and H. Nitka, Transformations of solid H₂S, *Phys. Z.* **37**, 435 (1936). [X-ray lattice parameters. 20 to 150 °K. In German.]
- ^TKan, L. S., and B. G. Lazarev, A low temperature X-ray camera, *Zhur. Tekh. Fiz.* **21**, 1542 (1951). [20 °K and up. In Russian.]
- Keesom, W. H., F. P. G. van Agt, and A. F. J. Jansen, The thermal expansion of copper between +101° and -253 °C, *Leiden Comm. No. 182a* (1926).
- *Keesom, W. H., and A. Bijl, The thermal expansion of Jena glass 16 III, *Leiden Comm. No. 203a* (1929). [20 to 373 °K.]
- Keesom, W. H., and D. W. Doborzynski, Measurements by the interferometric method on the thermal expansion of Jena glass 2954 III down to 4°K, *Physica* **1**, 1089-1102 (1934). [4 to 373 °K. Includes silica glass, 4 to 20 °K.]
- *Keesom, W. H., and D. W. Doborzynski, Measurements on the thermal expansion of Jena thermometer glass 2954 III by the method of the vertical comparator, *Physica* **1**, 1085-8 (1934). [20 to 373 °K.]
- Keesom, W. H., and A. F. J. Jansen, The thermal expansion of silver between +101 °C and -253 °C, *Leiden Comm. No. 185c* (1927).
- Keesom, W. H., and J. W. L. Kohler, New determination of the lattice constant of carbon dioxide, *Physica* **1**, 167 (1933). [Ag, CO₂. 83 °K.]
- Keesom, W. H., and J. W. L. Kohler, The lattice constant and expansion coefficient of solid carbon dioxide, *Physica* **1**, 655 (1933-4). [20 to 114 °K.]
- ^TKeith, H. D., An x-ray study in high-vacuum of the structure of evaporated copper films, *Proc. Phys. Soc. B* **69**, 180 (1956). [90 °K and up.]
- *Kelly, F. M., and W. B. Pearson, The rubidium transition at ~180 °K, *Can. J. Phys.* **33**, 17-24 (1955). [X-ray lattice parameter, 77 to 297 °K.]
- Keyston, J. R. G., J. D. MacPherson, and E. W. Guptill, Coefficient of thermal expansion of barium titanate, *Rev. Sci. Instr.* **30**, 246-8 (1959). [BaTiO₃, brass, Cu. 81 to 373 °K.]
- Kirby, R. K., Thermal expansion of polytetrafluoroethylene (Teflon) from -190° to +300°C, *J. Research NBS* **57**, 91-4 (1956).
- *Kittel, C., Note on the correlation through anharmonic force theory of the compressibility modulus and thermal expansion coefficient of KBr at low temperatures, *J. Chem. Phys.* **16**, 850 (1948). [Theoret.]
- *Kondo, K., On the properties of ferromagnetic alloy of manganese and bismuth at low temperature, I. Magnetic, dilatometric and calorimetric studies, *J. Phys. Soc. Japan* **5**, 26-30 (1950). [MnBi. 115 to 273 °K. In English.]
- König, H., A cubic modification of ice, *Z. Krist.* **105**, 279-286 (1944). [~170 °K. In German.]

- *Krishnan, R. S., and R. Srinivasan, Thermal expansion of cesium bromide, *Proc. Phys. Soc.* **B69**, 679-682 (1956). [134 to 574 °K.]
- Krupkowski, M. A., Nickel-copper alloys, *Rev. mét.* **26**, 193-208 (1929). [20 to 717 °K. In French.]
- Krupkowski, A., and W. J. de Haas, Thermo-electric and dilatation determinations with Ni-Cu alloys at low temperatures, *Leiden Comm. No. 194b* (1928). [Cu, Ni, Cu-Ni alloys. 20 to 283 °K.]
- *Kusmann, A., M. Auwarter, and G. Grfn. von Rittberg, The iron-platinum Invars and their expansion anomalies, *Ann. Physik* **4**, 174-182 (1948). [123 to 1000 °K. In German.]
- Laquer, H. L., and E. L. Head, Low temperature thermal expansion of plastics, *AECU-2161* (1952). *Tech. Inform. Serv., A.E.C., Oak Ridge, Tenn.* [20 Plastics. 20 to 300 °K.] To be published.
- *Lazarev, B. G., and A. I. Sudovtsov, Change of volume of tin in the superconducting transition in a magnetic field, *Dokl. Akad. Nauk S.S.S.R.* **69**, 345 (1949). [In Russian.]
- ^TLeibfried, G., A mechanical arrangement for measuring small changes in length, *Z. Physik* **127**, 580-7 (1950).
- *Lifshitz, I. M., Thermal properties of chain and laminar structures at low temperatures, *Zhur. Eksp. i Teoret. Fiz.* **22**, 475-486 (1952). [Theoret. In Russian.]
- Lindemann, C. L., Temperature dependence of the thermal coefficient of expansion, *Phys. Z.* **12**, 1197-99 (1911). [Al, Cu, Zn, Ag, Pb. 20 to 292 °K. In German.]
- Lindemann, C. L., Temperature dependence of the thermal coefficient of expansion. II., *Phys. Z.* **13**, 737-9 (1912). [NaCl, quartz, glass, B₂O₃. 20 to 300 °K. In German.]
- Lisgarten, N. D., and M. Blackman, The cubic form of ice, *Nature* **178**, 39-40 (1956). [93 °K and up.]
- Lonsdale, K., The structure of ice, *Proc. Roy. Soc.* **247**, 424-434 (1958). [H₂O, D₂O. Review.]
- *Lonsdale, K., and W. Hume-Rothery, The lattice spacings of lithium at 20 °C and -183 °C, *Phil. Mag.* **36**, 799-801 (1945).
- ^TLonsdale, K., and H. Smith, X-ray crystal photography at low temperatures, *J. Sci. Instr.* **18**, 133 (1941). [90 °K region.]
- Lucks, C. F., and H. W. Deem, Thermal properties of thirteen metals, *ASTM Special Tech. Publ. No. 227* (1958). [Aluminum 2024-T4 and 7075-T6, Inconel, Inconel-X, magnesium AN-M-29, K-Monel, SAE 1010 steel, stainless steels 301, 316, and 347. 116 °K and up.]
- Maass, O., and W. H. Barnes, Some thermal constants of solid and liquid carbon dioxide, *Proc. Roy. Soc.* **A111**, 224-244 (1926). [90 to 193 °K.]
- *Mader, H., The mechanical and physical properties of pure aluminum and some aluminum alloys at the temperature of liquid oxygen, *Metall* **5**, 1-5, Jan. 1951. [Alloys with 3, 5, 7, and 9% Mg. 150 to 673 °K. In German.]
- Masunoto, H., On the thermal expansion of alloys of cobalt, iron and chromium, and a new alloy "Stainless-Invar", *Sci. Repts. Tohoku Univ.* **23**, 265-280 (1934). [83 to 450 °K. In English.]
- McLennan, J. C., J. F. Allen, and J. O. Wilhelm, On the dilatation of superconductors, *Trans. Roy. Soc. Can. (III)* **25**, 1-12 (1931). [Pb, Rose's metal. 4 to 20 °K.]
- McLennan, J. C., and R. J. Monkman, On the thermal expansion of zinc and cadmium crystals and on the crystal structure of erbium and niobium, *Trans. Roy. Soc. Can. (III)* **23**, 255-67 (1929). [83 to 291 °K.]
- McSkimin, H. J., Measurement of elastic constants at low temperatures by means of ultrasonic waves—Data for silicon and germanium single crystals, and for fused silica, *J. Appl. Phys.* **24**, 988-997 (1953). [Ge. 70 to 335 °K.]
- ^TMichels, A., T. Wassenaar, and T. N. Swietering, A method for the measurement of the thermal expansion of solids between 0 and -180 °C, *Physica* **19**, 371 (1953). [Optical lever.]
- Mikura, Z., Contribution of the conduction electrons in a metal to the thermal expansion, *Proc. Phys.-Math. Soc. Japan* **23**, 309-18 (1941). [Theoret. In English.]
- Miller, P. H., and B. R. Russell, Effect of internal strains on linear expansion, X-ray lattice constant, and density of crystals, *J. Appl. Phys.* **23**, 1163 (1952). [Theoret.]
- Miller, P. H., and B. R. Russell, Effect on distribution of lattice defects within crystals of linear expansion and x-ray lattice constant, *J. Appl. Phys.* **24**, 1248-9 (1953). [Letter. Theoret.]
- Molby, F. A., The linear expansion of Invar steel between 100 °C and -190 °C, *Phys. Rev.* **35**, 79-80 (1912).
- Molby, F. A., Index of refraction and coefficients of expansion of optical glasses at low temperatures, *J. Opt. Soc. Am.* **39**, 600-611 (1949). [14 glasses. 79 to 373 °K.]
- *Muller, A., The crystal structure of the normal paraffins at temperatures ranging from that of liquid air to the melting points, *Proc. Roy. Soc. A* **127**, 417-430 (1930). [C₅H₁₂ to C₃₀H₆₂. X-ray lattice parameters.]
- Nitka, H., Debye-Scherrer patterns of germanium between 20 ° and 1110 ° Abs., *Phys. Z.* **38**, 896 (1937). [In German.]
- *Nix, F. C., and D. MacNair, A dilatometric study of the order-disorder transformation in Cu-Au alloys, *Phys. Rev.* **60**, 320-9 (1941). [83 °K and up.]
- ^TNix, F. C., and D. MacNair, An interferometric-dilatometer with photographic recording, *Rev. Sci. Instr.* **12**, 66-70 (1941). [Quartz. 83 to 930 °K.]
- Nix, F. C., and D. MacNair, The thermal expansion of pure metals: copper, gold, aluminum, nickel, and iron, *Phys. Rev.* **60**, 597-605 (1941). [81 to 300 °K.]
- Nix, F. C., and D. MacNair, The thermal expansion of pure metals. II: molybdenum, palladium, silver, tantalum, tungsten, platinum, and lead, *Phys. Rev.* **61**, 74-78 (1942). [85 to 300 °K.]
- *Okamura, T., On the transformation of magnetite at a low temperature, *Sci. Repts. Tokoku Univ.* **21**, 231-241 (1932). [89 to 173 °K. In English.]
- Olsen, J. L., and H. Rohrer, The volume change at the superconducting transition, *Helv. Phys. Acta* **30**, 49-66 (1957). [Sn, Pb, In, Tl, Ta. In English.]
- Onnes, H. K., and J. Clay, On the measurement of very low temperatures. X. Coefficient of expansion of Jena glass and of platinum between +16° and -182°. *Leiden Comm. No. 95b* (1906). [91 to 289 °K.]
- *Onnes, H. K., and W. Heuse, On the measurement of very low temperatures. V. The expansion coefficient of Jena and Thuringer glass between +16° and -182° C. *Leiden Comm. No. 85* (1903). [Jena glass 16 III, Thuringer glass No. 50.]
- ^TOwen, E. A., and G. I. Williams, A low-temperature x-ray camera, *J. Sci. Instr.* **31**, 49-54 (1954). [Ag, Fe. 79 to 291 °K.]
- *Owen, E. A., and G. I. Williams, X-ray measurements on lithium at low temperatures, *Proc. Phys. Soc.* **A67**, 895-900 (1954). [79 to 293 °K.]
- *Pearson, W. B., Thermal expansion of lithium, 77° to 300 °K, *Can. J. Phys.* **32**, 708-713 (1954).
- *Pearson, W. B., A handbook of lattice spacings and structures of metals and alloys, Pergamon Press (1958). [Handbook and compilation.]
- ^TPost, B., R. S. Schwartz, and I. Fankuchen, An improved device for x-ray diffraction studies at low temperatures, *Rev. Sci. Instr.* **22**, 218 (1951). [80 °K and up.]
- Potter, R. F., Elastic moduli of indium antimonide, *Phys. Rev.* **103**, 47-50 (1956). [83 to 523 °K.]
- Powell, R. W., Preliminary measurements of the thermal conductivity and expansion of ice, *Proc. Roy. Soc.* **247**, 464-6 (1958). [78 to 273 °K.]
- Reed, R. P., and R. P. Mikesell, The stability of austenitic stainless steels at low temperatures as determined by magnetic measurements, *Advances in Cryogenic Eng.* **4**, 84-100 (1958). Plenum Press.
- ^TRobertson, J. H., X-ray diffraction by single crystals at low temperatures: a cryostat for use with liquid hydrogen, *J. Sci. Instr.* **37**, 41-5 (1960).
- Rontgen, W. C., Linear thermal expansion coefficients of cuprite and diamond, *Sitzber. math.-physik. Kl. koniglich bayer. Akad. Wiss. Munich* (1912) pp. 381-7. [85 to 351 °K. In German.]

- Rosenfield, A. R., and B. E. Averbach, The effect of stress on the expansion coefficient, *J. Appl. Phys.* **27**, 154 (1956).
- Rubin, T., H. W. Altman, and H. L. Johnston, Coefficients of thermal expansion of solids at low temperatures. I. The thermal expansion of copper from 15 to 300 °K, *J. Am. Chem. Soc.* **76**, 5289-93 (1954).
- *Ruhemann, B., Temperature dependence of the lattice constants of MnO, *Phys. Z. Sowjetunion* **7**, 590-607 (1935). [77 to 300 °K. In German.]
- † Ruhemann, B., X-ray cameras for low temperatures, *Phys. Z. Sowjetunion* **7**, 572-582 (1935). [20 °K and up. In German.]
- *Ruhemann, B., and F. Simon, Crystal structures of krypton, xenon, hydrogen iodide and hydrogen bromide as functions of temperature, *Z. physik. Chem.* **B15**, 389 (1932) and **B16**, 408 (1932). [21 to 125 °K. In German.]
- Sapper, A., and W. Biltz, Molecular and atomic volumes. 31. Low temperature densities of some elements, *Z. anorg. u. allgem. Chem.* **198**, 184-190 (1931). [Hg, Cl₂, Br₂, I₂, Ca, S, P. 78 °K and up. In German.]
- † Saunders, J. B., Improved interferometric procedure with application to expansion measurements, *J. Research NBS* **23**, 179-195 (1939).
- † Saunders, J. B., Interferometer measurements on the expansion of iron, *J. Research NBS* **33**, 75-85 (1944). [285 to 674 °K.]
- Schad, L. W., and P. Hidnert, Preliminary determination of the thermal expansion of molybdenum, *BS Sci. Pap.* **15**, 31-40 (1919). [131 to 578 °K.]
- *Schallamach, A., X-ray investigation of the structure transition of methane at the λ point, *Proc. Roy. Soc. A171*, 569-578 (1939). [14 to 35 °K.]
- † Scheel, K., Apparatus for expansion determination by the Fizeau method at the temperature of liquid air, *Z. Instrumentenk.* **24**, 285 (1904). [In German.]
- Scheel, K., The expansion of quartz glass, *Verhandl. deut. physik. Ges.* **9**, 718-721 (1907). [83 to 373 °K. In German.]
- Scheel, K., Expansion of solids, especially of quartz in the direction of its principal axis, platinum, palladium, and quartz-glass at the temperature of liquid air, *Verhandl. deut. physik. Ges.* **9**, 3-23 (1907). [83 to 373 °K. In German.]
- Scheel, K., Thermal expansion of several substances. I., *Z. Physik* **5**, 167-172 (1921). [Jena glasses 16 III and 59 III, Berlin porcelain, 90 Pt 10 Ir, two Invars. 82 to 273 °K. In German.]
- Scheel, K., and W. Heuse, Determination of the expansion of platinum between -183° and room temperature with the comparator and Fizeau apparatus, *Verhandl. deut. physik. Ges.* **9**, 449-459 (1907). [In German.]
- Scheel, K., and W. Heuse, The absolute expansion of quartzglass at the temperature of liquid hydrogen, *Verhandl. deut. physik. Ges.* **16**, 1-3 (1914). [20 to 373 °K. In German.]
- *Schuch, A. F., and H. L. Laquer, Low temperature thermal expansion of uranium, *Phys. Rev.* **86**, 803 (1952). [Letter. 20 to 300 °K.]
- Scott, R. B., (1933), private communication.
- Shallcross, F. V., and G. B. Carpenter, X-ray diffraction study of the cubic phase of ice, *J. Chem. Phys.* **26**, 782-4 (1957). [83 °K and up.]
- Shearer, J. S., Note on coefficients of expansion at low temperature, *Phys. Rev.* **20**, 52-3 (1905). [Al, Ag. 93 to 273 °K.]
- Siegel, S., and S. L. Quimby, The thermal expansion of crystalline sodium between 80 °K and 290 °K, *Phys. Rev.* **54**, 76-8 (1938).
- Simmons, R. O., and R. W. Balluffi, Low temperature thermal expansion of copper, *Phys. Rev.* **108**, 278-80 (1957). [8 to 100 °K.]
- Simmons, R. O., and R. W. Balluffi, X-ray and expansion effects produced by imperfections in solids: Deuteron-irradiated germanium, *J. Appl. Phys.* **30**, 1249-1258 (1959). [Al. 595 to 930 °K.]
- Simmons, R. O., and R. W. Balluffi, Measurements of equilibrium vacancy concentrations in silver, *Bull. Am. Phys. Soc.* **5**, 181 (1960). [Abstract. 287 to 1229 °K.]
- Simon, F., and R. Bergmann, Thermally excited quantum jumps in solids. IV. Thermal expansion in the region of the anomaly, *Z. physik. Chem.* **B8**, 255-280 (1930). [Li, Si, Fe, steel, Ni, Cu, NH₄Cl, NH₄Br, (NH₄)₃PO₄. 85 to 300 °K. In German.]
- † Simon, F., and C. von Simson, The crystal structure of hydrogen chloride, *Z. Physik* **21**, 168 (1924). [81 to 107 °K. In German.]
- *Simon, F., and E. Vohsen, Crystal structure determination of the alkali metals and strontium, *Z. physik. Chem.* **133**, 165 (1928). [X-ray lattice constant of Li, Na, K, Rb, Cs, Sr at 100 °K. In German.]
- Smith, R. C., Determination of the difference between macroscopic and microscopic thermal coefficients of expansion for ionic crystals, Thesis, North Carolina State College (1954). ASTIA Document No. AD 37750. [NaCl, KCl, KBr. 293 to 373 °K.]
- Sosman, R. B., The properties of silica, The Chemical Catalog Co. Inc., New York, N.Y. (1927) Ch. 20. [Review.]
- Souder, W. and P. Hidnert, Measurements on the thermal expansion of fused silica, *BS Sci. Pap.* **21**, 1-23 (1926). [148 to 1273 °K.]
- † Steward, E. G., Ch. 10, Low-temperature methods, pp. 265-277 in "X-ray diffraction by polycrystalline materials", Eds. H. S. Peiser, H. P. Rooksby, and A. J. C. Wilson, The Institute of Physics, London (1955).
- *Stewart, J. W., and R. I. La Rock, Compression and densities of four solidified hydrocarbons and carbon tetrafluoride at 77 °K, *J. Chem. Phys.* **28**, 425-7 (1958). [Ethane, ethylene, propane, propylene, CF₄.]
- Swenson, C. A., Compression of the alkali metals to 10,000 atmospheres at low temperature, *Phys. Rev.* **99**, 423-430 (1955). [Li, Na, K, Rb, Cs. 4.2 and 77 °K.]
- Swenson, C. A., Properties of indium and thallium at low temperatures, *Phys. Rev.* **100**, 1607-14 (1955). [4 to 300 °K.]
- Thewlis, J., and A. R. Davey, Thermal expansion of grey tin, *Nature* **174**, 1011 (1954). [Letter. 143 to 293 °K.]
- Thewlis, J., and A. R. Davey, Thermal expansion of diamond, *Phil. Mag.* **1**, 409-14 (1956). [123 to 1200 °K.]
- Tool, A. Q., and J. B. Saunders, Expansion effects shown by some Pyrex glasses, *J. Research NBS* **40**, 67-83 (1948). [293 °K and up.]
- Toupin, R. A., and R. S. Rivlin, Dimensional changes in crystals caused by dislocations, *J. Mathematical Phys.* **1**, 8-15 (1960). [Theoret.]
- Trepus, G. E., R. S. Roper, W. R. Hickman, and J. T. Mitchell, Design data for "O"-rings and similar elastic seals, WADC Tech. Report 56-272 Part IV (1959). [Rubbers. 78 to 293 °K.]
- *Trombe, F., and M. Foex, Dilatometric study and determination of the allotropic states of metallic lanthanum and cerium, *Compt. rend.* **217**, 501-3 (1943). [78 to 673 °K. In French.]
- *Trombe, F., and M. Foex, Regions of existence and properties of the allotropic states of metallic cerium, *Ann. de Chim.* **19**, 417-445 (1944). [78 to 773 °K. In French.]
- *Trombe, F., and M. Foex, Dilatometric study of metallic neodymium, *Compt. rend.* **232**, 63-5 (1951). [78 to 923 °K. In French.]
- *Trombe, F., and M. Foex, Dilatometric study of metallic gadolinium, *Compt. rend.* **235**, 42-4 (1952). [78 to 573 °K. In French.]
- *Trombe, F., and M. Foex, Dilatometric study of metallic dysprosium, *Compt. rend.* **235**, 163-5 (1952). [78 to 573 °K. In French.]
- *Trombe, F., and M. Foex, Dilatation anomalies of the ferromagnetic rare earth metals gadolinium and dysprosium, *J. recherches centre natl. recherche sci.* **5**, 71-5 (1953). [Gd, La, Nd, Dy. 78 °K and up. In French.]

- *Ubbelohde, A. R., and I. Woodward, Structure and thermal properties associated with some hydrogen bonds in crystals. VII. Behavior of KH_2PO_4 and KH_2AsO_4 on cooling, *Proc. Roy. Soc.* **A188**, 358-371 (1947). [80 to 293 °K. Illustrates expansion anomaly at the ferroelectric Curie point.]
- Valentiner, S., and J. Wallot, Dependence of the expansion coefficients of solids on the temperature, *Ann. Physik* **46**, 837-867 (1915). [Pt, Ir, Rh, Si, fluorite, pyrite, Invar, fused quartz. 81 to 290 °K. In German.]
- ^T Vanderman, E. J., Microformer dilatometer, *Rev. Sci. Instr.* **22**, 757 (1951).
- *Varley, J. H. O., The thermal expansion of pure metals and the possibility of negative coefficients of volume expansion, *Proc. Roy. Soc.* **A237**, 413 (1956). [Theoret.]
- Visvanathan, S., Thermal expansion at low temperatures, *Phys. Rev.* **81**, 626 (1951). [Letter. Theoret.]
- ^T Viswamitra, M. A., and S. Ramaseshan, Simple device for growing crystals at low temperatures in x-ray cameras, *Rev. Sci. Instr.* **31**, 456-7 (1960).
- Wagner, C., and J. Beyer, Electrical conductivity and the unit cell in silver bromide, *Z. physik. Chem.* **B32**, 113 (1936). [293 to 673 °K. In German.]
- Walker, P. L., H. A. McKinstry, and C. C. Wright, X-ray diffraction studies of a graphitized carbon, *Ind. Eng. Chem.* **45**, 1711 (1953). [77 to 1400 °K.]
- Ward, J. O., M. D. Jepson, and J. R. Rait, Effect of alloying elements on the breakdown of austenite at sub-zero temperatures, *J. Iron Steel Inst.* **170**, 1 (1952).
- Werner, A., Thermal expansion of mild and hardened steel, *Z. Instrumentenk.* **44**, 315-320 (1924). [21 steels. 73 to 423 °K. In German.]
- Winter-Klein, A., Variation of the expansion coefficient of glass at low temperature, *Compt. rend.* **230**, 1857-8 (1950). [Borosilicate crown, light flint. 90 °K and up. In French.]
- ^T Wood, L. A., N. Bekkedahl, and C. G. Peters, Application of the interferometer to the measurement of dimensional changes in rubber, *J. Research NBS* **23**, 571-583 (1939). ["Stark" rubber. 88 to 320 °K.]
- ^T Work, R. N., A photoelectric recording interferometer for measurement of dimensional changes, *J. Research NBS* **47**, 80 (1951).
- Wunnenberg, E., W. Fischer, and A. Sapper, Molecular and Atomic Volumes. 24. Techniques of volumetric measurements of low temperature solids, *Z. physik. Chem.* **151**, 1-12 (1930). [Thuringian glass, Bi, calcite, KCl. 78 °K. In German.]
- *Wyckoff, R. W. G., Crystal structures, Interscience Publ. Inc. [A loose-leaf compilation including lattice parameters, issuance of which began in 1948.]
- *Zollweg, R. J., X-ray lattice constant of barium oxide, *Phys. Rev.* **100**, 671-3 (1955). [8 to 435 °K.]

BOULDER, COLO., December 8, 1960.

THE NATIONAL BUREAU OF STANDARDS

The scope of activities of the National Bureau of Standards at its major laboratories in Washington, D.C., and Boulder, Colo., is suggested in the following listing of the divisions and sections engaged in technical work. In general, each section carries out specialized research, development, and engineering in the field indicated by its title. A brief description of the activities, and of the resultant publications, appears on the inside of the front cover.

WASHINGTON, D.C.

Electricity. Resistance and Reactance. Electrochemistry. Electrical Instruments. Magnetic Measurements. Dielectrics.

Metrology. Photometry and Colorimetry. Refractometry. Photographic Research. Length. Engineering Metrology. Mass and Scale. Volumetry and Densimetry.

Heat. Temperature Physics. Heat Measurements. Cryogenic Physics. Equation of State. Statistical Physics.

Radiation Physics. X-Ray, Radioactivity. Radiation Theory. High Energy Radiation. Radiological Equipment. Nucleonic Instrumentation. Neutron Physics.

Analytical and Inorganic Chemistry. Pure Substances. Spectrochemistry. Solution Chemistry. Analytical Chemistry. Inorganic Chemistry.

Mechanics. Sound. Pressure and Vacuum. Fluid Mechanics. Engineering Mechanics. Rheology. Combustion Controls.

Organic and Fibrous Materials. Rubber. Textiles. Paper. Leather. Testing and Specifications. Polymer Structure. Plastics. Dental Research.

Metallurgy. Thermal Metallurgy. Chemical Metallurgy. Mechanical Metallurgy. Corrosion. Metal Physics. Electrodeposition.

Mineral Products. Engineering Ceramics. Glass. Refractories. Enameled Metals. Crystal Growth. Constitution and Microstructure.

Building Research. Structural Engineering. Fire Research. Mechanical Systems. Organic Building Materials. Codes and Safety Standards. Heat Transfer. Inorganic Building Materials.

Applied Mathematics. Numerical Analysis. Computation. Statistical Engineering. Mathematical Physics.

Data Processing Systems. Components and Techniques. Digital Circuitry. Digital Systems. Analog Systems. Applications Engineering.

Atomic Physics. Spectroscopy. Radiometry. Solid State Physics. Electron Physics. Atomic Physics.

Instrumentation. Engineering Electronics. Electron Devices. Electronic Instrumentation. Mechanical Instruments. Basic Instrumentation.

Physical Chemistry. Thermochemistry. Surface Chemistry. Organic Chemistry. Molecular Spectroscopy. Molecular Kinetics. Mass Spectrometry. Molecular Structure and Radiation Chemistry.

• Office of Weights and Measures.

BOULDER, COLO.

Cryogenic Engineering. Cryogenic Equipment. Cryogenic Processes. Properties of Materials. Gas Liquefaction.

Ionosphere Research and Propagation. Low Frequency and Very Low Frequency Research. Ionosphere Research. Prediction Services. Sun-Earth Relationships. Field Engineering. Radio Warning Service.

Radio Propagation Engineering. Data Reduction Instrumentation. Radio Noise. Tropospheric Measurements. Tropospheric Analysis. Propagation-Terrain Effects. Radio-Meteorology. Lower Atmosphere Physics.

Radio Standards. High Frequency Electrical Standards. Radio Broadcast Service. Radio and Microwave Materials. Atomic Frequency and Time Interval Standards. Electronic Calibration Center. Millimeter-Wave Research. Microwave Circuit Standards.

Radio Systems. High Frequency and Very High Frequency Research. Modulation Research. Antenna Research. Navigation Systems. Space Telecommunications.

Upper Atmosphere and Space Physics. Upper Atmosphere and Plasma Physics. Ionosphere and Exosphere Scatter. Airglow and Aurora. Ionospheric Radio Astronomy.

